

Synthetic aging study of Ni-30Cu (a.k.a. Ni₃₀Cu).

Aging at 700 C for 8 h in air raised Vickers hardness
from 210 HV to 246 HV (method HV10).

Performed by the Synthetic metallurgy team, resistance furnace.

Conclusion dated 2024-09-12.