Nanocarriers for targeted drug delivery

Benefits and challenges of nanotechnology for medicine

Russell Maguire

ENGI4131 Advanced Semiconductor Devices

Durham University

December 3, 2018



Nanocarriers




Figure 1: General structure of a nanocarrier, including the optional active targeting ligands.

A nanocarrier is a biocompatible nanoparticle encapsulating a drug, with size of the order 1 nm to 100 nm.

Nanocarriers provide a range of improvements over free drugs, including reduced toxicity and immunogenic response; longer circulation time; and improved solubility.

This is achieved using encapsulants with a hydrophilic surface; typically phospholipids or polymers which form stable single layer micelles and bilayer liposomes suspended in water and blood. Drug conjugates are distinct in that the active drug is covalently bonded to a protein, polymer or antibody.

Polyethylene glycol (PEG) is a hydrophilic polymer which has been shown to mask immunogens such as the phospholipids used to build liposomes [1], resulting in a new class of nanoparticles—immunoliposomes.

However employing nanocarriers for drug delivery raises additional challenges: new toxic side-effects; biodegradability; the cost and complexity of formulation.

polymeric

micelle liposome micelle liposome



drug

conjugate

immuno-

Figure 2: Structure of common types of organic nanocarriers ■ hydrophobic/lipophilic, ■ hydrophilic

Targeted drug delivery




Figure 3: Effect of drug distribution in healthy and diseased tissue when using drugs targeted to a specific diseased tissue

The goal of targeted drug delivery is to maximise therapeutic benefit and minimise side-effects by increasing the concentration ratio of the active drug in the diseased tissue compared to healthy tissue.

The textbook example of targeted drug delivery is chemotherapy for tumour treatment.

Targeted drug delivery can be divided into three categories: first generation passive targeting, next generation stimuli-responsive targeting and active targeting.

target cell

Figure 7: Receptor-mediated endocytosis. In order: nanocarrier

Small tumours and blood cancers can be targeted by

encouraging cell uptake through receptor-mediated endo-

cytosis, where high-affinity ligands attached to nanocar-

riers are targeted to receptors common in specific cancer

After binding with a receptor, the cell wall absorbs the

nanoparticle forming an acidic pocket in the cell called

an endosome [9]. pH-responsive nanocarriers have been

designed to release their payload in this environment [7].

Common targeting ligands include folic acid, carbohy-

To a certain extent, active targeting is still dependent

on the EPR effect to reach the vicinity of the cancers

cells without binding to cells in healthy tissue.

and drug release 4

binding 1, endocytosis 2, endosome transport 3,

Active targeting

Passive targeting




Figure 4: The differences between lymphatic system drainage and blood vessel permeability in healthy tissue and solid tumours

Passive targeting is dominated by the enhanced permeability and retention effect (EPR effect) whereby nanoscale particles can accumulate preferentially in solid tumours, first noticed by Maeda *et al.* [2].

First generation approved nanomedicines [3] rely on the EPR effect.

Permeable blood vessels in solid tumours let nutrients and nanoscale particles easily cross the endothelium. Padera *et al.* discovered rapidly proliferating cancer cells compress lymph vessels [4], retaining nanopaticles by preventing the tumour from easily draining.

However, limitations include poor deep tumour penetration and ineffective small tumour targeting. Jain and Stylianopoulos describe methods for overcoming this barrier [5].

Example

- Doxin[®]/Caelyx[®] was the first nanocarrier medicine, approved in 1995 for chemotherapy [6].
- *Doxorubicin* is the active compound, encapsuled in a *PEG*ylated immunoliposome.
- Benefits include reduced cardiac side effects and increased circulation time [3].

Stimuli-responsive targeting

In passive targeting, nanocarriers are allowed to break down at the target site releasing the drug, but efficacy can be improved using stimuli triggered release.




Figure 5: Polymeric micelles with pH-responsive polymers that readily protonate as pH falls, or deprotonate as pH increases, resulting in destructive charge imbalances [7]

Internal stimuli are bioindicators of disease and locality, including pH, temperature, redox potential and enzymes.

For example, solid tumours have been observed with a lower pH than healthy tissue [8, 9].




Figure 6: Liposomes modified with thermosensitive polymers which deform at hyperthermic temperatures, disrupting the liposome barrier [10, 11]

External stimuli can be applied electric or magnetic fields, ultrasound, heat and light.

Hyperthermia can be induced by applying direct heat until the tumour reaches 40 °C to 45 °C [12, 13]. Alternatively iron-oxide containing nanoparticles can be used to convert oscillating magnetic fields into heat [14].

Example

drates and antibodies.

cells.

- Variations of Doxin®/Caelyx® with anti-EGFR targeting ligands are in clinical trials [15].
- Targets the epidermal growth factor receptors (EGFR) on rapidly proliferating cancer cells.
- 11. K. Kono, *Advanced drug delivery reviews* **53**, 307–319 (2001).
- 12. S. Ganta *et al.*, Journal of controlled release **126**, 187–204 (2008).
- 13. A. Jhaveri et al., Journal of controlled release 190, 352-370 (2014).
- 14. F. Scherer et al., Gene therapy **9**, 102 (2002).
- 15. C. Mamot et al., The lancet oncology **13**, 1234–1241 (2012).

- J. M. Harris, R. B. Chess, *Nature reviews Drug discovery* 2, 214 (2003).
 H. Maeda *et al.*, *Journal of controlled release* 65, 271–284 (2000).
- 3. A. Wicki et al., Journal of controlled release 200, 138–157 (2015).
- T. P. Padera *et al.*, *Nature* **427**, 695 (2004).
- 5. R. K. Jain, T. Stylianopoulos, *Nature reviews Clinical oncology* **7**, 653 (2010).
- M. Harrison et al., Journal of clinical oncology 13, 914–920 (1995).
 T. Sun et al., Angewandte Chemie International Edition 53,
- 12320–12364 (2014).
- 9. L. E. Gerweck, K. Seetharaman, *Cancer research* **56**, 1194–1198 (1996).

I. F. Tannock, D. Rotin, Cancer research 49, 4373-4384 (1989).

.0. T. Ta, T. M. Porter, *Journal of controlled release* **169**, 112–125 (2013). 1