

SGCC QA Production Testing Audit Log Report

Record Type: Tempered (Center Punch Break Test)

Generated: 8/10/2026, 11:03:06 PM | Date Range: All to All

Entry #1 - Date: 2026-08-10 16:00:00 | SGCC #: CUS01CA

Type: TTG (Non-Pattern) | Thickness: 1/2" | Sample Size: 34x76

Specimen Weight: 117.600 lbs | Max Particle Wt: 206.400g | Actual 10-Pc Wt: 207.000g

Operator: admin | Result: FAIL



Entry #2 - Date: 2026-08-07 21:26:00 | SGCC #: CUS01CA

Type: TTG (Non-Pattern) | Thickness: 3/16" | Sample Size: 34x76

Specimen Weight: 44.100 lbs | Max Particle Wt: 77.400g | Actual 10-Pc Wt: 77.000g

Operator: admin | Result: PASS



Entry #3 - Date: 2026-08-07 21:17:00 | SGCC #: SGCC123

Type: TTG (Non-Pattern) | Thickness: 1/4" | Sample Size: 34x76

Specimen Weight: 58.800 lbs | Max Particle Wt: 103.200g | Actual 10-Pc Wt: 100.000g

Operator: admin | Result: PASS

Notes: TEST LOG

