



CONSUMER PRODUCTS SERVICES DIVISION

KONGES SLOEJD A/S

Technical Report: (5226)139-1010

Date Received: May 19, 2026

May 28, 2026

PAGE 1 OF 6

LINE GALSGAARD
KONGES SLOEJD A/S
KUGLEGARDSVEJ 13-17, BUILDING 13
COPENHAGEN 1434
DENMARK

Sample Description: PRINCESS CROWN COSTUME

Vendor: N/A

Manufacturer: N/A

Buyer: N/A

Labeled Age Grade: NOT PRESENT

Appropriate Age Grade: OVER 3 YEARS OF AGE

Client Specified Age: 3Y+

Grade:

Tested Age Grade: OVER 3 YEARS OF AGE

UPC Code: N/A

Sample Size: 1

Style No(s): KS103275

SKN/SKU No.: N/A

PO No.: PO000400

Ref #: N/A

Country of Origin: CHINA

Assortment No.: N/A

Country of Destination: EUROPE;UK

EXECUTIVE SUMMARY:

The sample(s) MEET the following requirement(s):

- The migration of certain elements in Category III - Scraped off toy material requirements of the European Standard, "Safety of Toys", EN 71 Part 3: 2019+A2:2024.

BUREAU VERITAS HONG KONG LIMITED

Lai Ka Yan, Margaret

Head of Operation

Toys and Juvenile Products Department

ML/dl

Bureau Veritas Hong Kong Limited
Kowloon Bay Office
1/F Pacific Trade Centre, 2 Kai Hing Road,
Kowloon Bay, Kowloon, Hong Kong
Tel: (852) 2331 0888 Fax: (852) 2331 0889
www.bureauveritas.com/cps

This report is governed by, and incorporates by reference, the Conditions of Testing as posted at the date of issuance of this report at <http://www.bureauveritas.com/home/about-us/our-business/cps/about-us/terms-conditions/> and is intended for your exclusive use. Any copying or replication of this report to or for any other person or entity, or use of our name or trademark, is permitted only with our prior written permission. This report sets forth our findings solely with respect to the test samples identified herein. The results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. Our report includes all of the tests requested by you and the results thereof based upon the information that you provided to us. Measurement uncertainty is only provided upon request for accredited tests. Statements of conformity are based on simple acceptance criteria without taking measurement uncertainty into account, unless otherwise requested in writing. You have 60 days from date of issuance of this report to notify us of any material error or omission caused by our negligence or if you require measurement uncertainty; provided, however, that such notice shall be in writing and shall specifically address the issue you wish to raise. A failure to raise such issue within the prescribed time shall constitute your unqualified acceptance of the completeness of this report, the tests conducted and the correctness of the report contents.

The result(s) apply to the sample(s) as received.
The location of performance of the laboratory activities is defined as Kowloon Bay office unless specified.



RESULTS:

MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2019+A2:2024)

Test Method : European Standard EN 71 Part 3: 2019+A2:2024, Section 8 and 9.

Class: Category III - Scraped off toy material

Sample Identity	Color	Location	Style
A.	clear plastic	filament of sequins of crown	
B.	clear iridescent plastic	sequins of crown	
C.	white thread/ pink net fabric	wand wand, dress	
D.	dull pink net fabric/ glitter	wand, crown, dress	
E.	pink ribbon	wand	
F.	dull pink ribbon	rod of wand	
G.	pink felt/ glue	crown	
H.	flat pink net fabric	crown	
I.	pink fabric	crown	
J.	pink thread/ sharp pink fabric	dress inner dress	
K.	ivory thread/ shiny pink fabric/ glitter	label upper dress	
L.	bright pink thread/ white soft plastic	elastic band of dress	
M.	bright white thread/ dull white soft plastic	elastic cord of dress	
N.	translucent pink fabric	bag	
O.	bright pink ribbon	bag	



RESULTS:

MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2019+A2:2024)

Analyte	Requirement (mg/kg)	Result (mg/kg)					
		Sample ID					
	Category III	A.	B.	C.	D.	E.	F.
Aluminium (Al)	28130	LT 2	3	8	36	6	5
Arsenic (As)	47	LT 0.15	LT 0.15	LT 0.15	LT 0.15	LT 0.15	LT 0.15
Boron (B)	15000	LT 5	LT 5	LT 5	LT 5	LT 5	LT 5
Barium (Ba)	18750	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Cadmium (Cd)	17	LT 0.15	LT 0.15	LT 0.15	LT 0.15	LT 0.15	LT 0.15
Cobalt (Co)	130	0.0724	0.0713	0.0263	LT 2	LT 2	LT 2
Chromium III (Cr III)	460	0.0724	0.0713	0.0263	0.63	0.379	0.407
Chromium VI (Cr VI)	0.053	#LT 0.02	#LT 0.02	#LT 0.02	#LT 0.02	#LT 0.02	#LT 0.02
Copper (Cu)	7700	LT 2	12	LT 2	LT 2	LT 2	LT 2
Mercury (Hg)	94	LT 0.15	LT 0.15	LT 0.15	LT 0.15	LT 0.15	LT 0.15
Manganese (Mn)	15000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Nickel (Ni)	930	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Lead (Pb)	23	LT 0.2	LT 0.2	LT 0.2	LT 0.2	LT 0.2	LT 0.2
Antimony (Sb)	560	LT 2	LT 2	LT 2	LT 2	6	4
Selenium (Se)	460	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Tin (Sn)	180000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Organic tin	12	LT 0.55	LT 0.55	LT 0.55	LT 0.55	LT 0.55	LT 0.55
Strontium (Sr)	56000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Zinc (Zn)	46000	LT 5	18	LT 5	7	LT 5	6
Mass of trace amount (gram)		-	-	-	-	-	-
Conclusion		Pass	Pass	Pass	Pass	Pass	Pass



RESULTS:

MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2019+A2:2024)

Analyte	Requirement (mg/kg)	Result (mg/kg)					
		Sample ID					
		Category III	G.	H.	I.	J.	K.
Aluminium (Al)	28130	LT 2	5	6	3	13	5
Arsenic (As)	47	LT 0.15	LT 0.15	7	LT 0.15	LT 0.15	LT 0.15
Boron (B)	15000	LT 5	LT 5	LT 5	LT 5	LT 5	LT 5
Barium (Ba)	18750	LT 2	LT 2	LT 2	LT 2	LT 2	6
Cadmium (Cd)	17	LT 0.15	LT 0.15	LT 0.15	LT 0.15	LT 0.15	LT 0.15
Cobalt (Co)	130	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Chromium III (Cr III)	460	0.277	1.42	1.57	0.314	0.382	0.127
Chromium VI (Cr VI)	0.053	#LT 0.02	#LT 0.02	#LT 0.02	#LT 0.02	#LT 0.02	#LT 0.02
Copper (Cu)	7700	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Mercury (Hg)	94	LT 0.15	LT 0.15	LT 0.15	LT 0.15	LT 0.15	LT 0.15
Manganese (Mn)	15000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Nickel (Ni)	930	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Lead (Pb)	23	LT 0.2	LT 0.2	LT 0.2	LT 0.2	LT 0.2	LT 0.2
Antimony (Sb)	560	2	5	4	LT 2	3	LT 2
Selenium (Se)	460	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Tin (Sn)	180000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Organic tin	12	LT 0.55	LT 0.55	LT 0.55	LT 0.55	LT 0.55	LT 0.55
Strontium (Sr)	56000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Zinc (Zn)	46000	LT 5	LT 5	LT 5	LT 5	11	912
Mass of trace amount (gram)		-	-	-	-	-	-
Conclusion		Pass	Pass	Pass	Pass	Pass	Pass



RESULTS:

MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2019+A2:2024)

Analyte	Requirement (mg/kg)	Result (mg/kg)					
		Sample ID					
		Category III	M.	N.	O.		
Aluminium (Al)	28130	LT 2	LT 2	2			
Arsenic (As)	47	LT 0.15	LT 0.15	LT 0.15			
Boron (B)	15000	LT 5	LT 5	LT 5			
Barium (Ba)	18750	LT 2	LT 2	LT 2			
Cadmium (Cd)	17	LT 0.15	LT 0.15	LT 0.15			
Cobalt (Co)	130	LT 2	LT 2	LT 2			
Chromium III (Cr III)	460	0.0616	0.166	0.259			
Chromium VI (Cr VI)	0.053	#LT 0.02	#LT 0.02	#LT 0.02			
Copper (Cu)	7700	LT 2	LT 2	LT 2			
Mercury (Hg)	94	LT 0.15	LT 0.15	LT 0.15			
Manganese (Mn)	15000	LT 2	LT 2	LT 2			
Nickel (Ni)	930	LT 2	LT 2	LT 2			
Lead (Pb)	23	12	LT 0.2	LT 0.2			
Antimony (Sb)	560	LT 2	LT 2	3			
Selenium (Se)	460	LT 2	LT 2	LT 2			
Tin (Sn)	180000	LT 2	LT 2	LT 2			
Organic tin	12	LT 0.55	LT 0.55	LT 0.55			
Strontium (Sr)	56000	LT 2	LT 2	LT 2			
Zinc (Zn)	46000	197	LT 5	LT 5			
Mass of trace amount (gram)		-	-	-			
Conclusion		Pass	Pass	Pass			

mg/kg = milligrams per kilogram (ppm=parts per million)

** = Average of duplicate analysis*

Organic tin = migration of total organic tin is expressed as tributyl tin cation content in mg/kg

= Verified results (see note)

LT = Less Than

FR = Failed Result

Remark: - Results of Cr III and Cr VI were reported as sum of soluble Chromium content unless specified.

Note: If soluble chromium content exceeded the screening limits of soluble chromium (VI), the results were verified by
 - EN71 part 3:2019+A2:2024, Annex F

RESULTS:

