# KONGES SLOEJD A/S

**Technical Report:** **(5225)093-0777(A) (REVISION)** May 07, 2025

The revision is highlighted in bold and noted with an (*)

Date Received: April 03, 2025 

LINE GALSGAARD
KONGES SLOEJD A/S
KUGLEGARDSVEJ 13-17, BULDING 13
COPENHAGEN, 1434
DENMARK

| | | | |
|---|---|---|---|
| Sample Description: | SWORD AND SHIELD<br>1. ) PINK<br>2. ) MIDNIGHT NAVY | | |
| Vendor: | 10 FASHION LEVEL | Sample Size: | 10 |
| Manufacturer: | N/A | Style No(s): | KS104007,KS101505 |
| Buyer: | N/A | SKN/SKU No.: | N/A |
| Labeled Age Grade: | 24M+ | PO No.: | SWORD AND SHIELD |
| Appropriate Age Grade: | OVER 2 YEARS OF AGE | Ref #: | N/A |
| Client Specified Age Grade: | 2Y+ | Country of Origin: | CHINA |
| Tested Age Grade: | OVER 2 YEARS OF AGE | Assortment No.: | N/A |
| UPC Code: | 5715681129616, 5715404311533 | Country of Destination: | AUSTRALIA; CANADA ;EUROPE; UK; USA; JAPAN |
| Protocol No.: | KONG-TY-08000-GBL, CPSD-GB-08444-USA | Details of Revision: | REMOVE JAPAN TEST |

## EXECUTIVE SUMMARY:

The sample(s) MEET the following requirement(s):

- The migration of certain elements requirements of the AS/NZS Standard, “Safety of toys”, AS/NZS ISO 8124: Part 3: 2021 Amd 1:2023.
- The di(2-ethylhexyl) phthalate (DEHP) content requirement of Australia Competition and Consumer Act 2010, Consumer Protection Notice No. 11 of 2011.
- The soluble heavy metals content in plastic requirement of Canada Consumer Product Safety Act, Toys Regulations, SOR/2011-17 Sec. 27(a) with Amendment in SOR/2016-302.
- The heavy metals requirements of the European "Council Directive 94/62/EC of 20 December 1994 on packaging and packaging waste."
- The listed aromatic amines (azocolourants) content requirement of the European Regulation (EC) No. 1907/2006 of the Registration, Evaluation, Authorisation and Restriction of Chemicals (REACH) with its Latest Amendment, Annex XVII concerning the Restrictions on the manufacture, placing on the market and use of certain dangerous substances, preparations and articles, Item no. 43, Points 1 and 2.
- The cadmium content requirement of the European Regulation (EC) No. 1907/2006 of the Registration, Evaluation, Authorisation and Restriction of Chemicals (REACH), Annex XVII concerning the Restrictions on the manufacture, placing on the market and use of certain dangerous substances, preparations and articles, Item no. 23 (amended up to EU No. 2016/217).

**Bureau Veritas Hong Kong Limited**
**Kowloon Bay Office**
1/F Pacific Trade Centre, 2 Kai Hing Road,
Kowloon Bay, Kowloon, Hong Kong
Tel: (852) 2331 0888 Fax: (852) 2331 0889
www.bureauveritas.com/cps

This report is governed by, and incorporates by reference, the Conditions of Testing as posted at the date of issuance of this report at http://www.bureauveritas.com/home/about-us/our-business/cps/about-us/terms-conditions/ and is intended for your exclusive use. Any copying or replication of this report to or for any other person or entity, or use of our name or trademark, is permitted only with our prior written permission. This report sets forth our findings solely with respect to the test samples identified herein. The results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. Our report includes all of the tests requested by you and the results thereof based upon the information that you provided to us. Measurement uncertainty is only provided upon request for accredited tests. Statements of conformity are based on simple acceptance criteria without taking measurement uncertainty into account, unless otherwise requested in writing. You have 60 days from date of issuance of this report to notify us of any material error or omission caused by our negligence or if you require measurement uncertainty; provided, however, that such notice shall be in writing and shall specifically address the issue you wish to raise. A failure to raise such issue within the prescribed time shall constitute your unqualified acceptance of the completeness of this report, the tests conducted and the correctness of the report contents.

The result(s) apply to the sample(s) as received.
The location of performance of the laboratory activities is defined as Kowloon Bay office unless specified.

**(*) EXECUTIVE SUMMARY:**

The sample(s) MEET the following requirement(s):

- The migration of certain elements in Category III - Scraped off toy material requirements of the European Standard, “Safety of Toys”, EN 71 Part 3: 2019+A2:2024.
- The pentachlorophenol (PCP) content requirement of the European Parliament and Council Regulation (EU) 2019/1021 on Persistent Organic Pollutants (POPs) (recast).
- The short chain chlorinated paraffins (SCCPs) content requirement of the European Parliament and Council Regulation (EU) 2019/1021 on Persistent Organic Pollutants (POPs) (recast).
- The azodyes (blue colorant) content requirement of the client’s specification (100mg/kg).
- The total lead content requirements of the Canada Consumer Product Safety Act, Consumer Products Containing Lead Regulations SOR/2018-83.

The style#(1) sample(s) MEET the following requirement(s):

- The small part requirement of 16 CFR 1501 (FHSA Regulations).
- Labeling requirements of “CE marking, manufacturer/ Importer name and address, and product identification” under “Directive 2009/48/EC Safety of Toy”.
- The flammability requirement of solids under ASTM F963-23 section 4.2 according to Annex A5, "Flammability testing procedure for solids and soft toys".
- The labeling requirements of ASTM F963-23, “Standard consumer safety specification for toy safety”.
- The mechanical hazards requirements of ASTM F963-23, “Standard consumer safety specification for toy safety”.
- The labelling requirement of the Consumer Product Safety Act section 14(a)(5), 15 U.S.C. §2063(a)(5) (CPSA) and Consumer Product Safety Improvement Act (CPSIA) of 2008 section 103 Tracking Labels for Children's Products.
- The mechanical and physical properties requirements of the tested subclauses of the European Standard, “Safety of toys”, EN71: Part 1:2014+A1:2018, clauses 1-7.
- The flammability requirements of the European Standard "Safety of Toys”, EN 71: Part 2: 2020.

**EXECUTIVE SUMMARY:**

The style#(1) sample(s) MEET the following requirement(s):

- The packaging and labeling requirements of the client's testing program.
- The performance requirement of client's specification.
- The phthalates (BBP, DBP, DEHP, DINP, DIBP, DPENP, DHEXP & DCHP) content requirements of ASTM F963-23, "Standard Consumer Safety Specification for Toy Safety," Section 4.3.8.
- The soluble heavy metals content in substrate requirements of ASTM F963-23, "Standard Consumer Safety Specification for Toy Safety," Section 4.3.5.2(2)(b).
- The BBP, DBP, DEHP, DnHP and DIDP content requirements in toys, child care articles and watches according to the California Proposition 65 settlements of County of Sacramento case number 07AS04683, and the Alameda Superior Court case numbers BG07350969, RG08367601, RG07351032 and RG08378050.
- The total lead content requirements in children products according to the California Proposition 65 settlements of Alameda Superior Court RG 07356892.
- The phthalates (BBP, DBP, DEHP, DINP, DIBP, DPENP, DHEXP & DCHP) content requirements of the Consumer Product Safety Improvement Act (CPSIA) of 2008 Sec. 108(a) and 108(c), 16 CFR 1307).
- The total lead content of 100ppm requirements by composite testing in substrate materials (Consumer Products Safety Improvement Act (CPSIA) of 2008).
- The total lead content of 90ppm requirements of 16 CFR 1303, "Ban of lead-containing paint and certain consumer products bearing lead-containing paint" as mandated by Congress in section 101(f) of the Consumer Products Safety Improvement Act (CPSIA) of 2008, Public Law 110-314.
- The heavy metals content in packaging requirements of Model Toxics Legislation of the Toxics in Packaging Clearinghouse, TPCH (formerly the Coalition of Northeastern Governors, CONEG).

Note: At the request of the client, the sample(s) was evaluated for use by children 2Y+.

Note: Based on visual evaluation and material breakdown received, there is no polyvinyl chloride (PVC) found in the samples submitted and thus the corresponding testing of the Canada Consumer Product Safety Act, Phthalates Regulations, SOR/2016-188 regarding to the restriction of use of certain phthalates content have not been conducted.

**EXECUTIVE SUMMARY:**

Note: According to the associated documents of Consumer Product Safety Improvement Act (CPSIA) of 2008, exemptions were granted to certain materials or products, such as natural materials / paper and similar materials / CMYK process printing inks / metal & alloys / electronics devices components / ordinary books / dyed & undyed textiles. Therefore, the lead content analysis of some components was not conducted.

Note: The received sample(s) contained surface coating(s) which are bonded to the substrate materials during the manufacturing process and cannot be scraped off for testing, therefore such coating material(s) was not subject to the heavy metals analysis of surface coating in ASTM F963-23, “Standard consumer safety specification on toy safety”, section 4.3.5.1(2).

Note: Exemptions were granted to certain materials or products, such as natural materials / paper and similar materials / CMYK process printing inks / metal & alloys / dyed & undyed textiles. Therefore, the lead content analysis of some components was not conducted.

BUREAU VERITAS HONG KONG LIMITED

Lai Ka Ming, Kent
Head of Technical Assurance
Toys and Juvenile Products Department

KL/ww

**RESULTS:**

**APPROPRIATE AGE GRADE DETERMINATION**

| | |
|---|---|
| The Appropriate Age Grade is determined with reference to the EN71: Part 1 : 2014 +A1:2018, CEN ISO/TR 8124-8:2016 Safety of toys - Part 8: Age Determination Guidelines prepared by Technical Committee CEN/TC 52 and Age Grade Determination Guidelines of the Consumer Product Safety Commission (CPSC). | |
| Note : | The most stringent age grade from the Labeled Age Grade and the Appropriate Age Grade will be used for testing. |
| Note : | If the client does not specify an age grade for testing or request Bureau Veritas Consumer Products Services, Inc. to determine an appropriate age grade, the labeled age grade will be used for testing. |

EXPLANATION OF THE ABBREVIATIONS FOR PART 1, 2

| Symbol | Explanation |
|---|---|
| NM | The sample(s) DOES NOT MEET the requirement of this Subclause |
| M | The sample(s) MEET the requirement of this Subclause |
| N/A | Not Applicable |
| NR | Not Requested |
| NE | Not Evaluated |
| NT | Not Tested |
| NP | None Present |
| P | Present |
| R | Refer to Comment Section of this report |

| Symbol | Language Present | Symbol | Language Present | Symbol | Language Present |
|---|---|---|---|---|---|
| B | Belgian language | G | German language | PR | Portuguese language |
| D | Danish language | GR | Greek language | S | Spanish language |
| E | English language | H | Dutch language | SD | Swedish language |
| F | Finnish language | I | Italian language | SZ | Swiss language |
| FR | French language | N | Norwegian language | | |

**RESULTS:**

**MECHANICAL & PHYSICAL PROPERTIES**
**(EN 71: PART 1 – 2014+A1 – 2018)**

| Subclause | Requirement | Result |
|---|---|---|
| 4.1 | Material cleanliness | M |
| 4.2 | Assembly | NA |
| 4.3 | Flexible plastic sheeting | NA |
| 4.4 | Toy Bags | NA |
| 4.5 | Glass | NA |
| 4.6 | Expanding materials | NA |
| 4.7 & 7.6 | Edges | M |
| 4.8 & 7.6 | Points and metallic wires | M |
| 4.8e | Splinters | M |
| 4.9 | Protruding parts | NA |
| 4.10.1 | Folding and sliding mechanisms | NA |
| 4.10.2 | Driving mechanisms | NA |
| 4.10.3 | Hinges | NA |
| 4.10.4 | Springs | NA |
| 4.11 | Mouth actuated toys and other toys intended to be put in the mouth | NA |
| 4.12 & 7.3 | Balloons | NA |
| 4.13 & 7.9 | Cord of toy kites and other flying toys | NA |
| 4.14.1 | Toys which a child can enter | NA |
| 4.14.2 & 7.8 | Masks and helmets | NA |
| 4.15.1 | Toys propelled by child | |
| 4.15.1.2 & 7.10.1 & 7.10.2 & 7.10.3 & 7.10.4 & 7.16 | Toys propelled by child – Instructions for use | NA |
| 4.15.1.3 | Toys propelled by child – Strength | NA |
| 4.15.1.4 | Toys propelled by child – Stability | NA |
| 4.15.1.5 | Toys propelled by child – Braking | NA |
| 4.15.1.6 | Toys propelled by child - Transmission | NA |
| 4.15.1.7 | Toys propelled by child – insertion mark | NA |
| 4.15.1.8 | Electrically-driven ride-on toys | NA |
| 4.15.2 | Toy bicycles | |
| 4.15.2.2 & 7.15 | Toy bicycles – Warnings and instructions for use | NA |
| 4.15.2.3 | Toy bicycles – Braking | NA |
| 4.15.3 & 7.16 & 7.19 | Rocking horses and similar toys | NA |
| 4.15.4 & 7.16 | Toys not propelled by child | NA |
| 4.15.5 & 7.18 | Toy scooters | NA |
| 4.16 | Heavy immobile toys | NA |

**RESULTS:**

**MECHANICAL & PHYSICAL PROPERTIES**
**(EN 71: PART 1 – 2014+A1 – 2018)**

| Subclause | Requirement | Result |
|---|---|---|
| 4.17.2 | All projectiles | NA |
| 4.17.3 & 7.7 | Projectile toys with stored energy | NA |
| 4.17.4 & 7.26 | Certain projectiles toys without stored energy | NA |
| 4.18 & 7.4 | Aquatic toys and inflatable toys | NA |
| 4.19 & 7.13 & 7.14 | Percussion caps | NA |
| 4.20.2.1-4.20.2.8, 4.20.2.10, 4.20.2.12 | Acoustics | NA |
| 4.20.2.9, 4.20.2.11 & 7.14 | Acoustics – percussion toys & cap-firing toys | NA |
| 4.21 | Toys containing a non-electrical heat source | NA |
| 4.22 & 7.2 | Small balls | NA |
| 4.23 | Magnet | |
| 4.23.2 a, b & c | Toy other than magnetic / electrical experimental sets intended for children over 8 years | NA |
| 4.23.3 & 7.20 | Magnetic / electrical experimental sets intended for children over 8 years | NA |
| 4.24 | Yo-yo ball | NA |
| 4.25 | Toys attached to food | NA |
| 4.26 | Toy Disguise Costumes | NA |
| 4.27.1 | Flying toys – General | NA |
| 4.27.2 & 7.25.1 | Rotors and propellers on flying toys | NA |
| 4.27.3 & 7.25.2 | Rotors and propellers on remote controlled flying toys | NA |
| | **FOR TOYS INTENDED FOR CHILDREN UNDER 36 MONTHS** | |
| 5.1 | General | M |
| 5.1a | Small parts – as received | M |
| 5.1b | Small parts, sharp points, sharp edges – after tests | M |
| 5.1c | Cross section <2mm metal points & wires | NA |
| 5.1e | Toys contain glue | NA |
| 5.1f | Casing of toys | NA |
| 5.2 | Fillings, coverings and seams | NA |
| 5.3 | Adhesion of plastic sheeting | NA |
| 5.4.2 | Cords and chains in toys intended for children under 18 months | NA |
| 5.4.3 & 7.22 | Cords and chains in toys intended for children of 18 months or over but under 36 months | NA |
| 5.4.4 | Fixed loops, tangled loops and nooses | M |
| 5.4.5 | Cords and chains on pull along toys | NA |
| 5.4.6 & 7.21 | Electrical cables | NA |
| 5.4.7 | Cross-sectional dimension of certain cords | NA |

**RESULTS:**

**MECHANICAL & PHYSICAL PROPERTIES**
**(EN 71: PART 1 – 2014+A1 – 2018)**

| Subclause | Requirement | Result |
|---|---|---|
| 5.4.8 | Self-retracting cords | NA |
| 5.4.9 & 7.11 & 7.23 | Toys attached to or intended to be strung across a cradle, cot or perambulator | NA |
| 5.5 & 7.12 | Liquid filled toys | NA |
| 5.6 | Electrically driven toys | NA |
| 5.7 | Glass and porcelain | NA |
| 5.8 | Shape and size | NA |
| 5.9 & 7.17 | Monofilament fibres | NA |
| 5.10 | Small balls | NA |
| 5.11 | Play figures | NA |
| 5.12 | Hemispheric shaped toys | NA |
| 5.13 | Suction cups | NA |
| 5.14 | Straps intended to be worn fully or partially around the neck | NA |
| 5.15 & 7.24 | Sledges with cords for pulling | NA |
| 6 | Packaging | NA |
| | **WARNINGS, INSTRUCTIONS FOR USE** | |
| 7.1 | General | M |
| 7.2 | Toys not intended for children under 36 months | NA |
| 7.5 | Functional toys | NA |

**RESULTS:**

**FLAMMABILITY (EN 71 PART 2: 2020)**

| Subclause | Requirement | Result |
|---|---|---|
| 4.1 | Cellulose nitrate | NP |
| 4.1 | Highly flammable solids | NP |
| 4.1 | Surface flash on a piled surface | NA |
| 4.1 | Flammable gases | NA |
| 4.1 | Extremely flammable liquids, highly flammable liquids, flammable liquids and flammable gels | NA |
| 4.2 | Toys to be worn on the head | NA |
| 4.3 | Toy disguise costumes and toys intended to be worn by child in play | NA |
| 4.3 | warning on product and packaging (10 - 30 mm/s) | NA |
| 4.4 | Toys intended to be entered by a child | NA |
| 4.4 | warning on product and packaging (10 – 30 mm/s) | NA |
| 4.5 | Soft-filled toys | NA |

**2009/48/EC GENERAL LABELING REQUIREMENT**

| Requirement | Result |
|---|---|
| CE Mark | M |
| Manufacturer/ Importer name and address | M |
| Product Identification | M |

*M = Meet NM = Not Meet N/A = Not Applicable R = Refer to Comment Section*

**RESULTS:**

## APPROPRIATE AGE GRADE DETERMINATION

| |
|---|
| The Appropriate Age Grade is determined with reference to the Age Determination Guidelines of the Consumer Product Safety Commission (CPSC); and the ASTM F963-23, "Standard Consumer Safety Specification for Toy Safety". Annex A1 |
| Note : The most stringent age grade from the Labeled Age Grade and the Appropriate Age Grade will be used for testing.<br><br>Note : If the client does not specify an age grade for testing or request Bureau Veritas Consumer Products Services, Inc. to determine an appropriate age grade, the labeled age grade will be used for testing. |

## USE AND ABUSE TESTS

The samples were undergo the tests in accordance with section 8.6 through 8.16, whichever is applicable

| Test | Test Parameters | Standard Reference |
|---|---|---|
| Impact Test | 4 x 3 ft | 1500.52(b) |
| Torque Test | 4 in-lbs | 1500.53(e) |
| Tension Test | 15 lbs | 1500.53(f) |
| Compression Test | 30 lbs | 1500.53(g) |

**RESULTS:**

**PHYSICAL AND MECHANICAL HAZARDS (ASTM F963-23)**

| Section | Requirement | Result |
|---|---|---|
| 4.1 | Material Quality | M |
| 4.3.7 | Stuffing Materials | N/A |
| 4.5 | Sound-producing Toys | N/A |
| 4.6 | Small Objects | M |
| 4.7 | Accessible Edges | M |
| 4.8 | Projections | N/A |
| 4.9 | Accessible Points | M |
| 4.10 | Wires and Rods | N/A |
| 4.11 | Nails and Fasteners | N/A |
| 4.12 | Plastic Film | N/A |
| 4.13 | Folding Mechanisms and Hinges | N/A |
| 4.14 | Cords, Straps and Elastics | N/A |
| 4.15 | Stability and Over-load Requirements | N/A |
| 4.16 | Confined Spaces | N/A |
| 4.17 | Wheels, Tires, and Axles | N/A |
| 4.18 | Holes, Clearances and Accessibility of Mechanisms | N/A |
| 4.19 | Simulated Protective Devices | N/A |
| 4.20 | Pacifiers | N/A |
| 4.21 | Projectile Toys | N/A |
| 4.22 | Teethers and Teething Toys | N/A |
| 4.23 | Rattles | N/A |
| 4.24 | Squeeze Toys | N/A |
| 4.25 | Battery-operated Toys<br>(exclude Section 4.25.9 Battery-powered ride-on toys & Section 4.25.10 Toys that Contain Secondary Cells or Secondary Batteries) | N/A |
| 4.26 | Toys Intended to be Attached to a Crib or Playpen | N/A |
| 4.27 | Stuffed and Beanbag-type Toys | N/A |
| 4.30 | Toy Gun Marking | N/A |
| 4.32 | Certain Toys with Nearly Spherical Ends | N/A |
| 4.34 | Small Balls | N/A |
| 4.35 | Pompoms | N/A |
| 4.36 | Hemispheric-shaped Objects | N/A |
| 4.37 | Yo Yo Elastic Tether Toys | N/A |
| 4.38 | Magnets | N/A |
| 4.39 | Jaw Entrapment in Handles and Steering Wheels | N/A |
| 4.40 | Expanding Materials | N/A |

*M = Meet  NM = Not Meet  N/A = Not Applicable  R = Refer to Comment Section*

**RESULTS:**

**LABELING AND INSTRUCTIONAL REQUIREMENT (ASTM F963-23)**

| Section | Requirement | Result |
|---|---|---|
| 5.1.2 | Tracking label | M |
| 5.4 & 5.3 | Aquatic Toys | N/A |
| 5.5 & 5.3 | Crib and Playpen Toys | N/A |
| 5.6 & 5.3 | Mobiles | N/A |
| 5.7 & 5.3 | Stroller and Carriage Toys | N/A |
| 5.8 & 5.3 | Toys Intended to be Assembled by an Adult | N/A |
| 5.9 & 5.3 | Simulated Protective Devices | N/A |
| 5.10 & 5.3 | Toys with Functional Sharp Edges or Sharp Points | N/A |
| 5.11 | Small Objects, Small Balls, Marbles and Balloons (16 CFR 1500.19) | N/A |
| 5.12 | Art Materials (16 CFR 1500.14(b)(8)) | N/A |
| 5.14 | Battery-Operated Toys (exclude 5.14.1 and 5.14.2) | N/A |
| 5.14.1 & 5.3 | Battery-Powered Ride-On Toys | N/A |
| 5.14.2 & 5.3 | Button or Coin Cell Batteries | N/A |
| 5.15 | Promotional Materials | M |
| 5.16 & 5.3 | Magnets | N/A |
| 6.1 | Definition and Description | M |
| 6.2 | Crib and Playpen Toys | N/A |
| 6.3 | Mobiles | N/A |
| 6.4 & 5.3 | Toys Intended to be Assembled by an Adult | N/A |
| 6.5 | Battery-Operated Toys | N/A |
| 6.6 | Battery-Powered Ride-On Toys | N/A |
| 6.7 | Toys in Contact with Food | N/A |
| 6.9 | Toys which require a manufacturer-supplied specialty or custom tool to access the battery(ies) | N/A |
| 7.1 | Producer's Name and Address | M |
| 7.2 | Battery-powered Ride-on Toys | N/A |

*M = Meet NM = Not Meet N/A = Not Applicable R = Refer to Comment Section*

**FLAMMABILITY (ASTM F963-23 section 4.2 according to Annex A5)**

| Requirement | Test Method Reference | Findings |
|---|---|---|
| Burn rate no greater than 0.1 of an inch per second | ASTM F963-23 section 4.2 according to Annex A5 | Ignited but Self-Extinguished. |

**RESULTS:**

**AROMATIC AMINES (AZOCOLOURANTS) CONTENT (European Regulation (EC) No. 1907/2006 REACH with its Latest Amendment, Annex XVII, Item no. 43, Points 1 and 2)**

Test Method: Quantification by Gas Chromatography/Mass Spectrometry (GC/MS)
Additional chromatographic technique employed to confirm positive result by HPLC/TLC

| Sample ID | Color / Component | Location | Style |
|---|---|---|---|
| A. | Composite of<br>shiny golden/ white knitted fabric | elastic band of shield | 1,2 |

| Test Parameter: | | Aromatic Amines (Azocolourants) | | |
|---|---|---|---|---|
| Requirement: | | 30 mg/kg | | |
| Sample ID | Test Method | Detected Amine Number | Concentration (mg/kg (ppm)) | Conclusion |
| A. | I | ND | ND | Pass |

*ND = Not Detected (Detection Limit = 5 mg/kg (ppm))* *ppm = parts per million*
*mg/kg = milligrams per kilogram* *NR = Not Requested*
** = The specimen is a minor component. As only a reduced mass (< 0.5 g) could be used for the test the result may have a greater uncertainty due to lower material homogeneity*

*Amine No. = Refer to List of Banned Amines for the description of the detected Amine.*
*Test Method I = European Standard EN ISO 14362-1: 2017, Clauses 9, 10.2 and afterwards.*
*Test Method II = European Standard EN ISO 14362-1: 2017, Clauses 9, 10.1, 10.3 and afterwards.*
*Test Method III = International Standard EN ISO 17234-1: 2015.*

*Remark:*
*The list of aromatic amines in azo colorants is summarized in table of Appendix.*
*The CAS-number 97-56-3 (no. 5) and 99-55-8 (no. 6) are further reduced to CAS-number 95-53-4 (no. 18) and 95-80-7 (no. 19), respectively.*
*The colorant(s) of Test Item(s), that are able to form 4-aminoazobenzene, is (are) able to generate aniline and 1,4-phenylenediamine under the condition of Test Method.*
*The absence of 4-aminoazobenzene is inferred by the absence of aniline and 1,4-phenylenediamine under the condition of Test Method.*

**RESULTS:**

**AROMATIC AMINES (AZOCOLOURANTS) CONTENT (European Regulation (EC) No. 1907/2006 REACH with its Latest Amendment, Annex XVII, Item no. 43, Points 1 and 2)**

| **LIST OF BANNED AMINES**<br>**Specified Amines** | | |
|---|---|---|
| Number | Chemical Name | CAS Number |
| 1. | 4-aminobiphenyl | 92-67-1 |
| 2. | Benzidine | 92-87-5 |
| 3. | 4-chloro-o-toluidine | 95-69-2 |
| 4. | 2-naphthylamine | 91-59-8 |
| 5. | o-aminoazotoluene | 97-56-3 |
| 6. | 5-nitro-o-toluidine | 99-55-8 |
| 7. | 4-chloroaniline | 106-47-8 |
| 8. | 4-methoxy-m-phenylenediamine | 615-05-4 |
| 9. | 4,4'-diaminodiphenylmethane | 101-77-9 |
| 10. | 3,3'-dichlorobenzidine | 91-94-1 |
| 11. | 3,3'-dimethoxybenzidine | 119-90-4 |
| 12. | 3,3'-dimethylbenzidine | 119-93-7 |
| 13. | 4,4'-methylenedi-o-toluidine | 838-88-0 |
| 14. | p-cresidine | 120-71-8 |
| 15. | 4,4'-methylene-bis-(2-chloro-aniline) | 101-14-4 |
| 16. | 4,4'-oxydianiline | 101-80-4 |
| 17. | 4,4'-thiodianiline | 139-65-1 |
| 18. | o-toluidine | 95-53-4 |
| 19. | 4-methyl-m-phenylenediamine | 95-80-7 |
| 20. | 2,4,5-trimethylaniline | 137-17-7 |
| 21. | o-anisidine | 90-04-0 |
| 22. | 4-amino azobenzene | 60-09-3 |

**RESULTS:**

**AZODYES (BLUE COLORANT) CONTENT (Client's Specification)**

| Parameter: | | | | Blue Colorant (CAS number: 118685-33-9) | |
|---|---|---|---|---|---|
| Required Limit: | | | | 100 mg/kg | |
| Test Component | | | | Result (mg/kg) | Conclusion |
| Color/Component | | Location | Style No. | | |
| A. | shiny golden/ white knitted fabric | elastic band of shield | 1,2 | LT 10 | Pass |

*ND = Not Detected (Detection Limit = 10 mg/kg (ppm))* *mg/kg (ppm) = milligrams per kilogram (parts per million)*
*LT = Less than*

**SHORT CHAIN CHLORINATED PARAFFINS (SCCPS) CONTENT (European Parliament and Council Regulation (EU) 2019/1021 on Persistent Organic Pollutants (POPs) (recast), Annex I, Part A)**

| Analyte | Short Chain Chlorinated Paraffins (SCCPs) | |
|---|---|---|
| Limit (mg/kg) | 1500 | |

| Analyte | | | | SCCPs | |
|---|---|---|---|---|---|
| Sample Description | | | | Result | Conclusion |
| | Color / Component | Location | Style | (mg/kg) | |
| (A) | clear blue plastic<br>deep grey/ deep blue/ black/ ivory/ golden/ beige printed grey foam/ glitter | gem of sword<br>sword, shield | 2<br>2 | LT 30 | Pass |
| (B) | clear pink plastic<br>transparent pink plastic | small gem of sword<br>large gem of sword | 1<br>1 | LT 30 | Pass |
| (C) | peach/ light yellow/ deep peach/ aqua green/ dark grey/ black/ white/ golden/ brown printed pink foam/ glitter<br>white elastic band | shield, sword<br>elastic band of shield | 1<br>1,2 | LT 30 | Pass |

*LT = Less Than* *mg/kg = milligrams per kilogram (ppm=parts per million)*
** = Average of duplicate analyses* *ND = None Detected (detection limit = 30 mg/kg)*

Remark:
Short chain chlorinated paraffins (SCCPs) is also known as alkanes C10-C13, chloro.
Plastics and leather of product(s) are applicable to be tested only.

**RESULTS:**

**PENTACHLOROPHENOL (PCP) CONTENT (European Parliament and Council Regulation (EU) 2019/1021 on Persistent Organic Pollutants (POPs) (recast), Annex I, Part A)**

| Analyte | PCP | |
|---|---|---|
| Limit (mg/kg) | None Detected | |

| Analyte | | | | PCP | |
|---|---|---|---|---|---|
| Sample Description | | | | Result | Conclusion |
| | Color / Component | Location | Style | (mg/kg) | |
| (A) | shiny golden/ white knitted fabric/ white elastic band | elastic band of shield | 1,2 | LT 0.05 | Pass |

*LT = Less Than*
** = Average of duplicate analyses*
*PCP = Pentachlorophenol*
*mg/kg = milligrams per kilogram (ppm=parts per million)*
*ND = None Detected (detection limit = 5 mg/kg)*

Remark:
Textiles, leather, wood/cord, paper and paperboard of product(s) are applicable to be tested only.

**DIETHYLHEXYL PHTHALATE (DEHP) CONTENT (Australia Competition and Consumer Act 2010, Consumer Protection Notice No. 11 of 2011)**

| Parameter: | | | | DEHP Content | |
|---|---|---|---|---|---|
| Maximum allowable limit: (% by weight) | | | | 1 | |
| Sample Description | | | | Result | Conclusion |
| | Color / Component | Location | Style | (% by weight) | |
| (A) | clear blue plastic | gem of sword | 2 | LT 0.005 | Pass |
| | deep grey printed grey foam | sword | 2 | | |
| | deep blue/ black/ ivory/ golden/ beige printed grey foam/ glitter | sword, shield | 2 | | |
| (B) | clear pink plastic | small gem of sword | 1 | LT 0.005 | Pass |
| | transparent pink plastic | large gem of sword | 1 | | |
| (C) | golden/ brown printed pink foam/ glitter | sword | 1 | LT 0.005 | Pass |
| | peach/ light yellow/ deep peach/ aqua green/ dark grey/ black/ white/ brown printed pink foam/ glitter | shield | 1 | | |

*Detection Limit :*
*DEHP = Diethylhexyl phthalate (0.005%)*
*LT = Less than*

**RESULTS:**

**PHTHALATES CONTENT IN CHILDREN`S TOYS AND CHILD CARE ARTICLES (Consumer Product Safety Improvement Act (CPSIA) of 2008, Section 108(a) and 108(c), 16 CFR 1307)**

**Test Method:** With reference to U. S. CPSC-CH-C1001-09.3 (April 1, 2010) / CPSC-CH-C1001-09.4 (January 17, 2018).

| Sample Identity | Color / Component | Location | Style |
|---|---|---|---|
| (A) | clear pink plastic | small gem of sword | 1 |
| | transparent pink plastic | large gem of sword | 1 |
| (B) | golden/ brown printed pink foam/ glitter | sword | 1 |
| | peach/ light yellow/ deep peach/ aqua green/ dark grey/ black/ white/ brown printed pink foam/ glitter | shield | 1 |
| (C) | white elastic band | elastic band of shield | 1 |

| Test Parameter: | Listed Phthalates (See Remark) | | |
|---|---|---|---|
| Requirement: | Each 0.1% | | |
| Sample ID | Detected Analyte | Concentration (%) | Conclusion |
| A. | ND | ND | Pass |
| B. | ND | ND | Pass |
| C. | ND | ND | Pass |

*Results reported in percentage*
*ND = None detected*
*Detection Limit: Each Phthalate (0.005%)*

| LIST OF RESTRICTED PHTHALATES | | |
|---|---|---|
| Number | Chemical Name | CAS Number |
| 1. | Butyl benzyl phthalate (BBP) | 85-68-7 |
| 2. | Dibutyl phthalate (DBP) | 84-74-2 |
| 3. | Di(2-ethylhexyl) phthalate (DEHP) | 117-81-7 |
| 4. | Di-iso-nonyl phthalate (DINP) | 28553-12-0 & 68515-48-0 |
| 5. | Di-iso-butyl phthalate (DIBP) | 84-69-5 |
| 6. | Di-n-pentyl phthalate (DPENP or DnPP) | 131-18-0 |
| 7. | Di-n-hexyl phthalate (DHEXP or DnHP) | 84-75-3 |
| 8. | Dicyclohexyl phthalate (DCHP) | 84-61-7 |

**RESULTS:**

**PHTHALATES CONTENT IN CHILDREN`S TOYS (ASTM F963-23, Section 4.3.8)**

**Test Method:** With reference to U. S. CPSC-CH-C1001-09.3 (April 1, 2010) / CPSC-CH-C1001-09.4 (January 17, 2018).

| Sample Identity | Color / Component | Location | Style |
|---|---|---|---|
| (A) | clear pink plastic | small gem of sword | 1 |
| | transparent pink plastic | large gem of sword | 1 |
| (B) | golden/ brown printed pink foam/ glitter | sword | 1 |
| | peach/ light yellow/ deep peach/ aqua green/ dark grey/ black/ white/ brown printed pink foam/ glitter | shield | 1 |
| (C) | white elastic band | elastic band of shield | 1 |

| Test Parameter: | Listed Phthalates (See Remark) | | |
|---|---|---|---|
| Requirement: | Each 0.1% | | |
| Sample ID | Detected Analyte | Concentration (%) | Conclusion |
| A. | ND | ND | Pass |
| B. | ND | ND | Pass |
| C. | ND | ND | Pass |

*Results reported in percentage*
*ND = None detected*
*Detection Limit: Each Phthalate (0.005%)*

| LIST OF RESTRICTED PHTHALATES | | |
|---|---|---|
| Number | Chemical Name | CAS Number |
| 1. | Butyl benzyl phthalate (BBP) | 85-68-7 |
| 2. | Dibutyl phthalate (DBP) | 84-74-2 |
| 3. | Di(2-ethylhexyl) phthalate (DEHP) | 117-81-7 |
| 4. | Di-iso-nonyl phthalate (DINP) | 28553-12-0 & 68515-48-0 |
| 5. | Di-iso-butyl phthalate (DIBP) | 84-69-5 |
| 6. | Di-n-pentyl phthalate (DPENP or DnPP) | 131-18-0 |
| 7. | Di-n-hexyl phthalate (DHEXP or DnHP) | 84-75-3 |
| 8. | Dicyclohexyl phthalate (DCHP) | 84-61-7 |

**RESULTS:**

**BBP/DBP/DEHP/DnHP/DIDP PHTHALATES CONTENT REQUIREMENTS IN TOYS, CHILD CARE ARTICLES AND WATCHES (California Proposition 65 settlements of County of Sacramento case number 07AS04683, and the Alameda Superior Court case numbers BG07350969, RG08367601, RG07351032 and RG08378050)**

| Color / Component | | Location | Style |
|---|---|---|---|
| | Composite of | | |
| (A) | clear pink plastic | small gem of sword | 1 |
| | transparent pink plastic | large gem of sword | 1 |
| (B) | golden/ brown printed pink foam/ glitter | sword | 1 |
| | peach/ light yellow/ deep peach/ aqua green/ dark grey/ black/ white/ brown printed pink foam/ glitter | shield | 1 |
| (C) | white elastic band | elastic band of shield | 1 |

| Test Parameter | BBP | DBP | DEHP | DnHP | DIDP | |
|---|---|---|---|---|---|---|
| Limit (%) | 0.1 | 0.1 | 0.1 | 0.1 | 0.1 | |
| Sample | Result (%) | | | | | Conclusion |
| A | LT 0.005 | LT 0.005 | LT 0.005 | LT 0.005 | LT 0.005 | Pass |
| B | LT 0.005 | LT 0.005 | LT 0.005 | LT 0.005 | LT 0.005 | Pass |
| C | LT 0.005 | LT 0.005 | LT 0.005 | LT 0.005 | LT 0.005 | Pass |

*Detection Limit :*
*BBP = Butyl benzyl phthalate (0.005%)*
*DBP = Dibutyl phthalate (0.005%)*
*DEHP = Di(2-ethylhexyl) phthalate (0.005%)*
*DnHP = Di-n-hexyl phthalate (0.005%)*
*DIDP = Di-iso-decyl phthalate (0.005%)*

*Results reported in percentage*
*LT = Less than*
*ND = None detected*

**RESULTS:**

**MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2019+A2:2024)**

Test Method : European Standard EN 71 Part 3: 2019+A2:2024, Section 9.

Class: Category III - Scraped off toy material

| Sample Identity | Color | Location | Style |
|---|---|---|---|
| A. | clear blue plastic | gem of sword | 2 |
| B. | deep grey printed grey foam | sword | 2 |
| C. | deep blue/ black/ ivory/ golden/ beige printed grey foam/ glitter | sword, shield | 2 |
| D. | clear pink plastic | small gem of sword | 1 |
| E. | transparent pink plastic | large gem of sword | 1 |
| F. | golden/ brown printed pink foam/ glitter | sword | 1 |
| G. | peach/ light yellow/ deep peach/ aqua green/ dark grey/ black/ white/ brown printed pink foam/ glitter | shield | 1 |
| H. | shiny golden/ white knitted fabric/ white elastic band | elastic band of shield | 1,2 |

**RESULTS:**

**MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2019+A2:2024)**

| Analyte | Requirement (mg/kg) | Result (mg/kg) | | | | | |
|---|---|---|---|---|---|---|---|
| | | Sample ID | | | | | |
| | Category III | A. | B. | C. | D. | E. | F. |
| Aluminium (Al) | 28130 | 7 | 6 | 31 | 2 | 5 | 6 |
| Arsenic (As) | 47 | LT 0.15 | LT 0.15 | LT 0.15 | LT 0.15 | LT 0.15 | LT 0.15 |
| Boron (B) | 15000 | LT 5 | LT 5 | LT 5 | LT 5 | LT 5 | LT 5 |
| Barium (Ba) | 18750 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 |
| Cadmium (Cd) | 17 | LT 0.15 | LT 0.15 | LT 0.15 | LT 0.15 | LT 0.15 | LT 0.15 |
| Cobalt (Co) | 130 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 |
| Chromium III (Cr III) | 460 | LT 0.02 | LT 0.02 | 0.0545 | LT 0.02 | 0.0217 | LT 0.02 |
| Chromium VI (Cr VI) | 0.053 | | | LT 0.02# | | | |
| Copper (Cu) | 7700 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | 22 |
| Mercury (Hg) | 94 | LT 0.15 | LT 0.15 | LT 0.15 | LT 0.15 | LT 0.15 | LT 0.15 |
| Manganese (Mn) | 15000 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 |
| Nickel (Ni) | 930 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 |
| Lead (Pb) | 23 | LT 0.2 | LT 0.2 | LT 0.2 | LT 0.2 | LT 0.2 | LT 0.2 |
| Antimony (Sb) | 560 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 |
| Selenium (Se) | 460 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 |
| Tin (Sn) | 180000 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 |
| Organic tin | 12 | LT 2 | LT 2 | LT 2 | 3 | LT 2 | LT 2 |
| Strontium (Sr) | 56000 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 |
| Zinc (Zn) | 46000 | LT 5 | 24 | 16 | 9 | 76 | 46 |
| Mass of trace amount (gram) | | --- | --- | --- | --- | --- | --- |
| Conclusion | | Pass | Pass | Pass | Pass | Pass | Pass |

**RESULTS:**

**MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2019+A2:2024)**

| Analyte | Requirement (mg/kg) | Result (mg/kg) | | | | | |
|---|---|---|---|---|---|---|---|
| | | Sample ID | | | | | |
| | Category III | G. | H. | | | | |
| Aluminium (Al) | 28130 | 8 | 5 | | | | |
| Arsenic (As) | 47 | LT 0.15 | LT 0.15 | | | | |
| Boron (B) | 15000 | LT 5 | LT 5 | | | | |
| Barium (Ba) | 18750 | LT 2 | LT 2 | | | | |
| Cadmium (Cd) | 17 | LT 0.15 | LT 0.15 | | | | |
| Cobalt (Co) | 130 | LT 2 | LT 2 | | | | |
| Chromium III (Cr III) | 460 | LT 0.02 | 0.0379 | | | | |
| Chromium VI (Cr VI) | 0.053 | | | | | | |
| Copper (Cu) | 7700 | LT 2 | LT 2 | | | | |
| Mercury (Hg) | 94 | LT 0.15 | LT 0.15 | | | | |
| Manganese (Mn) | 15000 | LT 2 | LT 2 | | | | |
| Nickel (Ni) | 930 | LT 2 | LT 2 | | | | |
| Lead (Pb) | 23 | LT 0.2 | LT 0.2 | | | | |
| Antimony (Sb) | 560 | LT 2 | LT 2 | | | | |
| Selenium (Se) | 460 | LT 2 | LT 2 | | | | |
| Tin (Sn) | 180000 | LT 2 | LT 2 | | | | |
| Organic tin | 12 | LT 2 | LT 2 | | | | |
| Strontium (Sr) | 56000 | LT 2 | LT 2 | | | | |
| Zinc (Zn) | 46000 | 13 | LT 5 | | | | |
| Mass of trace amount (gram) | | --- | --- | | | | |
| Conclusion | | Pass | Pass | | | | |

*mg/kg = milligrams per kilogram (ppm=parts per million)* *LT = Less Than*
** = Average of duplicate analysis* *FR = Failed Result*
*Organic tin = migration of total organic tin is expressed as tributyl tin cation content in mg/kg*
*# = Verified results (see note)*

Remark: - Results of Cr III and Cr VI were reported as sum of soluble Chromium content unless specified.
- Result(s) of organic tin was (were) calculated while assuming the tin content wholly contributed from tributyltin cation unless specified.

Note: If soluble chromium content or soluble tin content exceeded the screening limits of soluble chromium (VI) or organic tin content, the results were verified by below method
- Chromium VI: EN71 part 3:2019+A2:2024, Annex F
- Organic tin: EN71 part 3:2019+A2:2024, Annex G by Gas Chromatography – Mass Spectroscopy analysis.

**RESULTS:**

**CADMIUM CONTENT (European Regulation (EC) No. 1907/2006 REACH Annex XVII and its amendments up to Commission Regulation (EU) No. 2016/217, Item no. 23)**

| | | | | | | | |
|---|---|---|---|---|---|---|---|
| Category: | | | | Plastics | | | |
| Element: | | | | Cadmium | | | |
| Test Method | | | | BS EN 1122: 2001, Method B | | | |
| Maximum Allowable Limit: | | | | 100 mg/kg (0.01% by weight) | | | |
| Sample Description | | | | Reading 1 | Reading 2 | Average | Conclusion |
| Color / Component | | Location | Style | Result (mg/kg) | | | |
| (A) | clear blue plastic | gem of sword | 2 | LT 10 | LT 10 | LT 10 | Pass |
| | deep grey printed grey foam | sword | 2 | | | | |
| | deep blue/ black/ ivory/ golden/ beige printed grey foam/ glitter | sword, shield | 2 | | | | |
| (B) | clear pink plastic | small gem of sword | 1 | LT 10 | LT 10 | LT 10 | Pass |
| | transparent pink plastic | large gem of sword | 1 | | | | |
| (C) | golden/ brown printed pink foam/ glitter | sword | 1 | LT 10 | # | - | Pass |
| | peach/ light yellow/ deep peach/ aqua green/ dark grey/ black/ white/ brown printed pink foam/ glitter | shield | 1 | | | | |
| | white elastic band | elastic band of shield | 1,2 | | | | |

*LT = Less than* *mg/kg = milligrams per kilogram (ppm = parts per million)*

*# = Insufficient sample for duplicate analyses* *Operator: Chan Sai Kit, Tim*

**RESULTS:**

**HEAVY METALS PRESENT IN PACKAGING (European Council Directive 94/62/EC on Packaging and Packaging Waste)**

| | | | | | |
|---|---|---|---|---|---|
| Parameter: | The sum of lead, cadmium, mercury and hexavalent chromium | | | | |
| Maximum Allowable Limit: | - 600 ppm by weight after June 30, 1998<br>- 250 ppm by weight after June 30, 1999<br>- 100 ppm by weight after June 30, 2001 | | | | |
| Sample Description | | | | Result | Conclusion |
| Color/Component | | Location | Style | (mg/kg (ppm)) | |
| (A) | deep blue printed brown/ white carton/ adhesive | box | 2 | LT 20 | Pass |
| (B) | clear plastic/ glue | box | 1,2 | LT 20 | Pass |
| (C) | clear plastic sticker | circle tape | 1,2 | LT 20 | Pass |
| (D) | deep pink printed brown/ white carton/ adhesive | box | 1 | LT 20 | Pass |

*LT = Less Than*
*mg/kg = milligrams per kilogram (ppm = parts per million)*
** = Average of duplicate analyses*

**RESULTS:**

**MIGRATION OF CERTAIN ELEMENTS (AS/NZS ISO 8124 Part 3: 2021 Amd 1:2023)**

Test Method: Soluble heavy metals content analysis was determined by Inductively Coupled Plasma Spectrometry.

| Sample Identity | Color / Component | Location | Style |
|---|---|---|---|
| Any toy material given in Clause 1#, except modelling clay and putty, finger paint, and slime | | | |
| A. | clear blue plastic | gem of sword | 2 |
| B. | deep grey printed grey foam | sword | 2 |
| C. | deep blue/ black/ ivory/ golden/ beige printed grey foam/ glitter | sword, shield | 2 |
| D. | clear pink plastic | small gem of sword | 1 |
| E. | transparent pink plastic | large gem of sword | 1 |
| F. | golden/ brown printed pink foam/ glitter | sword | 1 |
| G. | peach/ light yellow/ deep peach/ aqua green/ dark grey/ black/ white/ brown printed pink foam/ glitter | shield | 1 |
| H. | shiny golden/ white knitted fabric/ white elastic band | elastic band of shield | 1,2 |

**RESULTS:**

**MIGRATION OF CERTAIN ELEMENTS (AS/NZS ISO 8124 Part 3: 2021 Amd 1:2023)**

| Analyte | As | B | Ba | Cd | Cr | Hg | Pb | Sb | Se |
|---|---|---|---|---|---|---|---|---|---|
| Any toy material given in Clause 1#, except modelling clay and putty, finger paint, and slime | 25 | - | 1000 | 75 | 60 | 60 | 90 | 60 | 500 |
| Modelling clay and putty | 25 | 3750 | 350 | 50 | 25 | 25 | 90 | 60 | 500 |
| Finger paint | 10 | - | 350 | 15 | 25 | 10 | 25 | 10 | 50 |
| Slime | 10 | 1250 | 350 | 15 | 25 | 10 | 25 | 10 | 50 |
| Analytical Correction | 60% | 60% | 30% | 30% | 30% | 50% | 30% | 60% | 60% |

| Analyte | As | B | Ba | Cd | Cr | Hg | Pb | Sb | Se | Mass of Trace Amount | Conclusion |
|---|---|---|---|---|---|---|---|---|---|---|---|
| Sample | Result (mg/kg) | | | | | | | | | (g) | |
| A. | LT 2 | - | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | | PASS |
| B. | LT 2 | - | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | | PASS |
| C. | LT 2 | - | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | | PASS |
| D. | LT 2 | - | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | | PASS |
| E. | LT 2 | - | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | | PASS |
| F. | LT 2 | - | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | | PASS |
| G. | LT 2 | - | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | | PASS |
| H. | LT 2 | - | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | | PASS |

*mg/kg = milligrams per kilogram (ppm=parts per million)*
*CR = adjusted analytical result*
*LT = Less Than*
** = Average of duplicate analysis*
*As = Arsenic, Ba = Barium, Cd = Cadmium,*
*Cr = Chromium, Hg = Mercury, Pb = Lead,*
*Sb = Antimony, Se = Selenium, B = Boron*
*# = coatings, polymeric materials, paper and paper board, textiles, glass/ceramic/metallic materials, other materials whether mass coloured or not, materials intended to leave a trace, pliable modeling materials – non-modelling clay, paints (excluding finger paint), powders & similar materials*

**RESULTS:**

**TOTAL LEAD CONTENT IN SURFACE COATING BY COMPOSITE TESTING ("Ban of Lead-containing paint and certain consumer products bearing Lead-containing paint", Consumer Product Safety Improvement Act (CPSIA) of 2008)**

**Test Method:** U.S. CPSC-CH-E1003.09.1:2011

| Element: | | | | Lead | | |
|---|---|---|---|---|---|---|
| Requirement: Maximum allowable limit: | | | | 90 mg/kg | | |
| Sample Description | | | | Result (mg/kg) | | Conclusion |
| | Color / Component | Location | Style | Overall | Potential | |
| (A) | golden coating/ glitter | sword | 1 | LT 10 | --- | Pass |
| (B) | peach/ light yellow/ deep peach/ aqua green/ dark grey/ black/ white coating | shield | 1 | LT 10 | --- | Pass |

*LT = Less Than*
** = Average of duplicate analyses*
*mg/kg = milligrams per kilogram (ppm = parts per million)*
*Potential = Estimated lead content per component is based on calculation by component individual weight*

**TOTAL LEAD CONTENT IN SUBSTRATE BY COMPOSITE TESTING (100PPM) (Consumer Product Safety Improvement Act (CPSIA) of 2008)**

**Test Method:** U.S. CPSC-CH-E1001-08.3:2012 or U.S. CPSC-CH-E1002-08.3:2012

| Analyte | Lead | |
|---|---|---|
| Requirement: Maximum allowable limit: | 100 mg/kg | |

| Analyte | | | | Lead (Pb) | Conclusion |
|---|---|---|---|---|---|
| Sample Description | | | | Result (mg/kg) | |
| | Color / Component | Location | Style | | |
| (A) | clear pink plastic<br>transparent pink plastic | small gem of sword<br>large gem of sword | 1<br>1 | LT 10 | Pass |
| (B) | golden/ brown printed pink foam/ glitter<br>peach/ light yellow/ deep peach/ aqua green/ dark grey/ black/ white/ brown printed pink foam/ glitter | sword<br>shield | 1<br>1 | LT 10 | Pass |

*LT = Less Than*
** = Average of duplicate analyses*
*mg/kg = milligrams per kilogram (ppm = parts per million)*

**RESULTS:**

**SOLUBLE HEAVY METALS CONTENT IN SUBSTRATE (ASTM F963-23, Section 4.3.5.2(2)(b))**

**Test Method:** ASTM International Standard ASTM F963-23, Section 8.3.5 (Excluding 8.3.5.5(3))

| Sample Identity | Color | Location | Style |
|---|---|---|---|
| A | clear pink plastic | small gem of sword | 1 |
| B | transparent pink plastic | large gem of sword | 1 |
| C | golden/ brown printed pink foam/ glitter | sword | 1 |
| D | peach/ light yellow/ deep peach/ aqua green/ dark grey/ black/ white/ brown printed pink foam/ glitter | shield | 1 |
| E | shiny golden/ white knitted fabric/ white elastic band | elastic band of shield | 1 |

| Analyte | As | Ba | Cd | Cr | Hg | Pb | Sb | Se |
|---|---|---|---|---|---|---|---|---|
| Max. Limit (mg/kg) | 25 | 1000 | 75 | 60 | 60 | 90 | 60 | 500 |
| Analytical Correction | 60% | 30% | 30% | 30% | 50% | 30% | 60% | 60% |

| Analyte | As | Ba | Cd | Cr | Hg | Pb | Sb | Se | Mass of Trace Amount | Conclusion |
|---|---|---|---|---|---|---|---|---|---|---|
| Sample | Result (mg/kg) | | | | | | | | (g) | |
| A | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | | Pass |
| B | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | | Pass |
| C | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | | Pass |
| D | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | | Pass |
| E | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | | Pass |

*mg/kg = milligrams per kilogram (ppm=parts per million)*
*CR = adjusted analytical result*
*LT = Less Than*
*ND = None Detected*

*As = Arsenic, Ba = Barium, Cd = Cadmium,*
*Cr = Chromium, Hg = Mercury, Pb = Lead,*
*Sb = Antimony, Se = Selenium*

Remark:
Textiles (natural or synthetic) are exempted for lead content requirement according to clarification of Toy Industry Association for ASTM F963-23. The lead content analysis result of corresponding material herein is for client's reference only.

**RESULTS:**

**Heavy Metals Content In Packaging – Model Toxics Legislation Of The Toxics In Packaging Clearinghouse (TPCH)**

| Analyte | Sum of Pb, Cd, Hg & Cr VI | |
|---|---|---|
| Requirement: Maximum allowable limit: | 100 mg/kg | |

| Analyte | | | | Sum of Pb, Cd, Hg & Cr VI | Conclusion |
|---|---|---|---|---|---|
| Sample Description | | | | Result (mg/kg) | |
| Color / Component | | Location | Style | | |
| (A) | deep pink printed brown/ white carton/ adhesive | box | 1 | LT 20 | PASS |
| (B) | clear plastic/ glue | box | 1 | LT 20 | PASS |
| (C) | clear plastic sticker | circle tape | 1 | LT 20 | PASS |

*LT = Less Than*
** = Average of duplicate analysis*
*mg/kg = milligrams per kilogram (ppm=parts per million)*
*Pb = Lead, Cd = Cadmium, Hg = Mercury, Cr VI = Hexavalent chromium*

*Remark:*
*The former name of the working group of this legislation was Coalition of Northeastern Governors (CONEG).*

**RESULTS:**

**TOTAL LEAD CONTENT IN CHILDREN PRODUCTS (California Proposition 65 settlements of Alameda Superior Court RG 07356892)**

Test Method: Acid digestion followed by Atomic Absorption Spectrophotometry or Inductively Coupled Plasma Spectrometry

| | | Maximum allowable limit | |
|---|---|---|---|
| Analyte | | Lead | |
| Type 1 | Paint and surface coatings | 90 mg/kg | |
| Type 2 | Substrate materials | 100 mg/kg | |

| Analyte | | | | Lead (Pb) | Conclusion |
|---|---|---|---|---|---|
| Sample Description | | | | Result (mg/kg) | |
| Color / Component | | Location | Style | | |
| Type 1: Paint and surface coatings | | | | | |
| (A) | golden coating/ glitter | sword | 1 | LT 10 | Pass |
| (B) | peach/ light yellow/ deep peach/ aqua green/ dark grey/ black/ white coating | shield | 1 | LT 10 | Pass |
| Type 2: Substrate materials | | | | | |
| (C) | clear pink plastic | small gem of sword | 1 | LT 10 | Pass |
| | transparent pink plastic | large gem of sword | 1 | | |
| (D) | golden/ brown printed pink foam/ glitter | sword | 1 | LT 10 | Pass |
| | peach/ light yellow/ deep peach/ aqua green/ dark grey/ black/ white/ brown printed pink foam/ glitter | shield | 1 | | |

*LT = Less Than* *mg/kg = milligrams per kilogram (ppm=parts per million)*
** = Average of duplicate analyses*

**RESULTS:**

**TOTAL LEAD CONTENT (Canada Consumer Product Safety Act – Consumer Products Containing Lead Regulations SOR/2018-83)**

Test Method: Health Canada, Product Safety Laboratory, Reference Manual, Book 5 - Laboratory Policies and Procedures – Part B: Test Method Section, Method C-02.2:2017, C-02.3:2017 or C-02.4-2017

| Analyte | Lead | |
|---|---|---|
| Requirement: Maximum allowable limit: | 90 mg/kg | |

| Analyte | | | | Lead (Pb) | |
|---|---|---|---|---|---|
| Sample Description | | | | Result | Conclusion |
| | Color / Component | Location | Style | (mg/kg) | |
| (A) | deep grey coating | sword | 2 | LT 10 | Pass |
| (B) | deep blue/ black/ ivory/ golden/ beige coating/ glitter | sword, shield | 2 | LT 10 | Pass |
| (C) | golden coating/ glitter | sword | 1 | LT 10 | Pass |
| (D) | peach/ light yellow/ deep peach/ aqua green/ dark grey/ black/ white coating | shield | 1 | LT 10 | Pass |
| (E) | clear blue plastic<br>deep grey printed grey foam | gem of sword<br>sword | 2<br>2 | LT 10 | Pass |
| (F) | deep blue/ black/ ivory/ golden/ beige printed grey foam/ glitter | sword, shield | 2 | LT 10 | Pass |
| (G) | clear pink plastic<br>transparent pink plastic | small gem of sword<br>large gem of sword | 1<br>1 | LT 10 | Pass |
| (H) | golden/ brown printed pink foam/ glitter<br>peach/ light yellow/ deep peach/ aqua green/ dark grey/ black/ white/ brown printed pink foam/ glitter | sword<br>shield | 1<br>1 | LT 10 | Pass |

*LT = Less Than*
** = Average of duplicate analyses*
*mg/kg =milligrams per kilogram (ppm=parts per million)*
*ND=Not detected*

**RESULTS:**

**SOLUBLE HEAVY METALS CONTENT IN PLASTIC (Canada Consumer Product Safety Act - Toys Regulations, SOR/2011-17 Sec. 27(a) with Amendment in SOR/2016-302)**

**Test Method:** ASTM International Standard ASTM F963-16, Section 8.3.5 (Excluding 8.3.5.5(3))

| Sample Identity | Color | Location | Style |
|---|---|---|---|
| A | clear blue plastic | gem of sword | 2 |
| B | deep grey printed grey foam | sword | 2 |
| C | deep blue/ black/ ivory/ golden/ beige printed grey foam/ glitter | sword, shield | 2 |
| D | clear pink plastic | small gem of sword | 1 |
| E | transparent pink plastic | large gem of sword | 1 |
| F | golden/ brown printed pink foam/ glitter | sword | 1 |
| G | peach/ light yellow/ deep peach/ aqua green/ dark grey/ black/ white/ brown printed pink foam/ glitter | shield | 1 |

| Analyte | As | Ba | Cd | Cr | Hg | Sb | Se |
|---|---|---|---|---|---|---|---|
| Maximum Limit (mg/kg) | 25 | 1000 | 75 | 60 | 60 | 60 | 500 |
| Analytical Correction | 60% | 30% | 30% | 30% | 50% | 60% | 60% |

| Analyte | As | Ba | Cd | Cr | Hg | Sb | Se | Mass of Trace Amount | |
|---|---|---|---|---|---|---|---|---|---|
| Sample | Result (mg/kg) | | | | | | | (g) | Conclusion |
| A. | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | | PASS |
| B. | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | | PASS |
| C. | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | | PASS |
| D. | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | | PASS |
| E. | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | | PASS |
| F. | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | | PASS |
| G. | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | LT 2 | | PASS |

*mg/kg = milligrams per kilogram (ppm=parts per million)*
**= Average of duplicate analysis*
*ND = Not detected*
*LT = Less Than*

*As = Arsenic, Ba = Barium, Cd = Cadmium,*
*Cr = Chromium, Hg = Mercury, Sb = Antimony,*
*Se = Selenium*
*Detection limit (mg/kg): Each element 2*

**RESULTS:**

| | | | |
|---|---|---|---|
| **Protocol Number** | KONG-TY-08000-GBL | **Version** | 26 |
| **Protocol Description** | TOYS | | |
| **Country** | All countries | | |
| **Scope** | The countries of distribution include Europe, United Kingdom, United States, Canada, Australia, Hong Kong, Japan, Korea.<br><br>**USA:**<br>Toy is defined as any object designed, manufactured, or marketed as a plaything for children under 14 years of age. Game consoles and it's associated accessories are defined as General Use Product unless it is embellished or decorated with childish themes or are marketed to children as per Interpretation of "Children's Product" - 16 CFR Part 1200 and will not be covered under this protocol.<br><br>**CAN:**<br>Toy is defined as a product that is intended for use by a child in learning or play intended for use by children under 14 years of age.<br><br>**EUR, GBR:**<br>This protocol is applicable to toys for children, toys being any product or material designed or intended whether or not exclusively, for use in play by children of less than 14 years.<br><br>This protocol does not cover buried trampoline<br>This protocol does not cover requirement for PPE covered under Directive 425/2016/EU. For a toy which is also a PPE, additional testing is required.<br><br>**AUS:**<br>Toy is any product or material designed or clearly intended for use in play by children less than 14 years of age.<br><br>**JPN:**<br>Toy is defined as any product or material designed or clearly intended for use in play by children under 14 years of age.<br>This protocol does not cover any food or cosmetic which comes with the toys.<br><br>**HKG:**<br>This protocol applies to toys<br>According to CAP 424 - Toys and Children's Products Safety Ordinance, schedule 1 toys shall meet the requirement in applicable ISO standards, IEC standards, EN standards or ASTM standards, as well as any additional safety requirement imposed by the Safety Authority.<br>This protocol only included the applicable ASTM standards for toys and additional safety requirement imposed by the Safety Authority.<br><br>Remark:<br>BV has no test capability for toys for Korea. For toy, testing can only be conducted by designated agency appointed by the Ordinance of Ministry of Trade, Industry and Energy, BVCPS is not one of them, lab need to subcontract to designated agency appointed by the Ordinance of Ministry of Trade, Industry and Energy for testing. | | |
| **Creation Date** | 16/Nov/2021 | **Last Revision Date** | 12/Nov/2024 |
| **Client Approval Date** | 13/Nov /2024 | **Approver** | Michelle Irani |

**RESULTS:**

| **Protocol Number** | KONG-TY-08000-GBL | **Version** | 26 |
|---|---|---|---|
| **No. of Sample for testing** | 3 | Dinnerware, Mugs, Pitchers, etc(decorated lip/rim): 12(18)<br>Product contain Fiber Content: 1 additonal<br>Product contain Care Label: Minimum additional 2 pcs and 1 additional pc for each care instruction<br>Toys with rechargeable battery : 5 additional<br>Electric/Battery Operated (per style)<br>Electric (per style with adapter/transformer)<br>Additional 6 for sunglasses and fashion spectacles | |
| **No. of Carton for transit testing** | 1 | | |
| **No. of Working Days for testing** | 10 | 19 workings days for toy with rechargeable battery<br>15 working days for EN 71-14 tests<br>12 working days for EN 71-8 tests<br>12 working days for AS/NZS 8124.6 tests | |

| **Keys** | | | | | |
|---|---|---|---|---|---|
| A | Additional Charge For This Test | | | R | Regulatory |

| | **Evaluation** | **Citation / Method** | **Criteria** | **Country** | **Result** | **Rating** |
|---|---|---|---|---|---|---|
| **PERFORMANCE** | | | | | | |
| | Actual use - functionality | Actual use / functionality | Shall function as intended as received.<br><br>Testing is limited to verification of basic function. Only function failures will be reported.<br><br>NT rating shall be given to product that cannot be tested due to testing cannot be replicated in laboratory conditions. | All Countries | M | Pass |

**RESULTS:**

SWORD AND SHIELD
Sample Number
(5225)093-0777

SWORD AND SHIELD
Sample Number
(5225)093-0777