CONSUMER PRODUCTS SERVICES DIVISION

KONGES SLOEJD A/S

Technical Report: **(5225)273-0714** October 09, 2025
Date Received: September 30, 2025

JENS PREBESEN
KONGES SLOEJD A/S
KUGLEGARDSVEJ 13-17, BULDING 13
COPENHAGEN, 1434
DENMARK

Sample Description:	PARTS OF FANS		
Vendor:	10 FASHION LEVEL TEN FASHION LIMITED	Sample Size:	1 LOT(S)
Manufacturer:	N/A	Style No(s):	KS104808
Buyer:	N/A	SKN/SKU No.:	N/A
Labeled Age Grade:	NOT PRESENT	PO No.:	#I/T
Appropriate Age Grade:	CHILDREN PRODUCTS, OVER 3 YEARS OF AGE	Ref #:	N/A
Client Specified Age Grade:	3Y+	Country of Origin:	CHINA
Tested Age Grade:	CHILDREN PRODUCTS, OVER 3 YEARS OF AGE	Assortment No.:	N/A
UPC Code:	N/A	Country of Destination:	Europe;USA

EXECUTIVE SUMMARY:

The sample(s) MEET the following requirement(s):

- The total lead content of 100ppm requirements by composite testing in substrate materials (Consumer Products Safety Improvement Act (CPSIA) of 2008).
- The migration of certain elements in Category III - Scraped off toy material requirements of the European Standard, “Safety of Toys”, EN 71 Part 3: 2019+A1:2021.
- The migration of certain elements in Category III - Scraped off toy material requirements of the European Standard, “Safety of Toys”, EN 71 Part 3: 2019+A2:2024.

BUREAU VERITAS HONG KONG LIMITED

Lai Ka Yan, Margaret
Head of Operation
Toys and Juvenile Products Department

ML/dl

Bureau Veritas Hong Kong Limited
Kowloon Bay Office
1/F Pacific Trade Centre, 2 Kai Hing Road,
Kowloon Bay, Kowloon, Hong Kong
Tel: (852) 2331 0888 Fax: (852) 2331 0889
www.bureauveritas.com/cps

This report is governed by, and incorporates by reference, the Conditions of Testing as posted at the date of issuance of this report at http://www.bureauveritas.com/home/about-us/our-business/cps/about-us/terms-conditions/ and is intended for your exclusive use. Any copying or replication of this report to or for any other person or entity, or use of our name or trademark, is permitted only with our prior written permission. This report sets forth our findings solely with respect to the test samples identified herein. The results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. Our report includes all of the tests requested by you and the results thereof based upon the information that you provided to us. Measurement uncertainty is only provided upon request for accredited tests. Statements of conformity are based on simple acceptance criteria without taking measurement uncertainty into account, unless otherwise requested in writing. You have 60 days from date of issuance of this report to notify us of any material error or omission caused by our negligence or if you require measurement uncertainty; provided, however, that such notice shall be in writing and shall specifically address the issue you wish to raise. A failure to raise such issue within the prescribed time shall constitute your unqualified acceptance of the completeness of this report, the tests conducted and the correctness of the report contents.

The result(s) apply to the sample(s) as received.
The location of performance of the laboratory activities is defined as Kowloon Bay office unless specified.

RESULTS:

TOTAL LEAD CONTENT IN SUBSTRATE BY COMPOSITE TESTING (100PPM) (Consumer Product Safety Improvement Act (CPSIA) of 2008)

Test Method: U.S. CPSC-CH-E1001-08.3:2012 or U.S. CPSC-CH-E1002-08.3:2012

Analyte	Lead	
Requirement: Maximum allowable limit:	100 mg/kg	

Analyte				Lead (Pb)	Conclusion
Sample Description				Result (mg/kg)	
Color / Component		Location	Style		
(A)	silvery metal	axle		LT 10	Pass
(B)	light silvery metal	end of axle		LT 10	Pass

LT = Less Than *mg/kg = milligrams per kilogram (ppm = parts per million)*
** = Average of duplicate analyses*

RESULTS:

RESULTS:

MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2019+A1:2021)

Test Method : European Standard EN 71 Part 3: 2019+A1:2021, Section 8 and 9.

Class: Category III - Scraped off toy material

Sample Identity	Color	Location	Style
A.	silvery metal	axle	
B.	light silvery metal	end of axle	

Analyte	Requirement (mg/kg)	Result (mg/kg)					
		Sample ID					
	Category III	A.	B.				
Aluminium (Al)	28130	LT 2	LT 2				
Arsenic (As)	47	LT 0.15	LT 0.15				
Boron (B)	15000	LT 5	LT 5				
Barium (Ba)	18750	LT 2	LT 2				
Cadmium (Cd)	17	LT 0.15	LT 0.15				
Cobalt (Co)	130	LT 2	LT 2				
Chromium III (Cr III)	460	0.0438	0.0454				
Chromium VI (Cr VI)	0.053	#LT 0.02	#LT 0.02				
Copper (Cu)	7700	25	85				
Mercury (Hg)	94	LT 0.15	LT 0.15				
Manganese (Mn)	15000	LT 2	LT 2				
Nickel (Ni)	930	LT 2	LT 2				
Lead (Pb)	23	LT 0.2	LT 0.2				
Antimony (Sb)	560	LT 2	LT 2				
Selenium (Se)	460	LT 2	LT 2				
Tin (Sn)	180000	27	43				
Organic tin	12	LT 0.55#	LT 0.55#				
Strontium (Sr)	56000	LT 2	LT 2				
Zinc (Zn)	46000	LT 5	10				
Mass of trace amount (gram)		-	-				
Conclusion		Pass	Pass				

RESULTS:

RESULTS:

MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2019+A1:2021)

mg/kg = milligrams per kilogram (ppm=parts per million) *LT = Less Than*
** = Average of duplicate analysis* *FR = Failed Result*
Organic tin = migration of total organic tin is expressed as tributyl tin cation content in mg/kg
 # = Verified results (see note)

Remark: - Results of Cr III and Cr VI were reported as sum of soluble Chromium content unless specified.
- Result(s) of organic tin was (were) calculated while assuming the tin content wholly contributed from tributyltin cation unless specified.

Note: If soluble chromium content or soluble tin content exceeded the screening limits of soluble chromium (VI) or organic tin content, the results were verified by below method
- Chromium VI: EN71 part 3:2019+A1:2021, Annex F
- Organic tin: EN71 part 3:2019+A1:2021, Annex G by Gas Chromatography – Mass Spectroscopy analysis.

RESULTS:

MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2019+A2:2024)

Test Method : European Standard EN 71 Part 3: 2019+A2:2024, Section 8 and 9.

Class: Category III - Scraped off toy material

Sample Identity	Color	Location	Style
A.	silvery metal	axle	
B.	light silvery metal	end of axle	

Analyte	Requirement (mg/kg)	Result (mg/kg)					
		Sample ID					
	Category III	A.	B.				
Aluminium (Al)	28130	LT 2	LT 2				
Arsenic (As)	47	LT 0.15	LT 0.15				
Boron (B)	15000	LT 5	LT 5				
Barium (Ba)	18750	LT 2	LT 2				
Cadmium (Cd)	17	LT 0.15	LT 0.15				
Cobalt (Co)	130	LT 2	LT 2				
Chromium III (Cr III)	460	0.0438	0.0454				
Chromium VI (Cr VI)	0.053	#LT 0.02	#LT 0.02				
Copper (Cu)	7700	25	85				
Mercury (Hg)	94	LT 0.15	LT 0.15				
Manganese (Mn)	15000	LT 2	LT 2				
Nickel (Ni)	930	LT 2	LT 2				
Lead (Pb)	23	LT 0.2	LT 0.2				
Antimony (Sb)	560	LT 2	LT 2				
Selenium (Se)	460	LT 2	LT 2				
Tin (Sn)	180000	27	43				
Organic tin	12	LT 0.55#	LT 0.55#				
Strontium (Sr)	56000	LT 2	LT 2				
Zinc (Zn)	46000	LT 5	10				
Mass of trace amount (gram)		-	-				
Conclusion		Pass	Pass				

RESULTS:

MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2019+A2:2024)

mg/kg = milligrams per kilogram (ppm=parts per million) *LT = Less Than*
** = Average of duplicate analysis* *FR = Failed Result*
Organic tin = migration of total organic tin is expressed as tributyl tin cation content in mg/kg
 # = Verified results (see note)

Remark: - Results of Cr III and Cr VI were reported as sum of soluble Chromium content unless specified.
- Result(s) of organic tin was (were) calculated while assuming the tin content wholly contributed from tributyltin cation unless specified.

Note: If soluble chromium content or soluble tin content exceeded the screening limits of soluble chromium (VI) or organic tin content, the results were verified by below method
- Chromium VI: EN71 part 3:2019+A2:2024, Annex F
- Organic tin: EN71 part 3:2019+A2:2024, Annex G by Gas Chromatography – Mass Spectroscopy analysis.

RESULTS: