HIC-LC3-24 Trial Protocol

Synthetic training content. Not a real Holcim trial report.

HIC-LC3-24 Trial Protocol

Owner: Holcim Innovation Centre (synthetic training)
Target plant: Loire Plant (synthetic)
Binder families in scope: CEM I control, CEM II/A-LL, LC3-50, LC3-35

1. Objective

Evaluate whether an LC3-style calcined-clay limestone binder can meet a 42.5 MPa 28-day class at a lower clinker factor than the CEM I control, and whether a subset of mixes can move to a plant-ready mix card for Loire Plant.

2. Methods

- EN 196-1 mortar cubes, 40 mm
- Water/binder ratio: 0.50
- Test ages: 1, 7, 28, and 90 days
- Fineness target for calcined clay: 4200 cm2/g Blaine
- 28-day spec strength: 42.5 MPa (CEM 42.5 class)
- Other ages have no numeric spec in this protocol

3. What this file does not contain

This protocol has methods and the spec only. It does not contain mix-by-mix compressive strengths. Those live in hic-lc3-24-interim-results.pdf.

4. Handover rule (methods view)

A mix may be considered for a plant mix card only after 28-day spec is met. Do not use 1-day cubes as the handover gate.

5. Brand rule

Do not describe this trial as ECOPlanet or ECOPact.