

PC-03 · EMULSIFIERS & THICKENERS · PERSONAL CARE

HS HEC 30000

Hydroxyethylcellulose

INCI	CAS	EC	FAMILY	SUPPLIED AS
Hydroxyethylcellulose	9004-62-0	—	PC-03	Powder

01 POSITIONING

Plant-derived rheology with the salt tolerance the reformulation wave needs.

02 HOW IT WORKS

01 Entanglement thickening

Dissolved chains entangle; viscosity scales with grade MW and dosage — no neutralization step.

02 Electrolyte immunity

Non-ionic ethers hold viscosity in brines that collapse carbomer gels.

03 Film & water retention

Dried films anchor actives; in wet systems, controls water migration.

03 APPLICATIONS

- Shampoos and salt-rich cleansers
- Lotions and creams
- Paints and construction (technical grades)
- Food systems (CMC, per grade)
- Tablet binding (HPMC, per grade)

04 FORMULATION GUIDE

USE LEVEL 0.3–2%

PH & CONDITIONS Stable pH 3–11

- Disperse in cold water (or slurry in glycerin) before heating to dissolve — prevents lumping.
- Choose grade by target viscosity at 1–2%: 3 000 for pourable, 30 000+ for gels.

05 TYPICAL SPECIFICATION

Appearance White to off-white powder

Viscosity (2%, 25 °C) per grade

Moisture ≤ 8%

Degree of substitution per TDS

Typical parameters. The specification on the current TDS and the per-lot Certificate of Analysis govern.

06 PERFORMANCE — DIRECTIONAL

Viscosity retention in 10% NaCl
Cellulose ether



Renewable-origin content
Cellulosics



Values are representative of the ingredient class, based on published technical literature, and shown directionally for comparison. Final performance must be validated in the customer's formulation.