



US-ML-JACKSON TN
801 GERDAU AMERISTEEL ROAD
JACKSON, TN 38305
USA

CERTIFIED MATERIAL TEST REPORT

CUSTOMER SHIP TO STEEL AND PIPE SUPPLY CO INC 1003 FORT GIBSON RD CATOOSA, OK 74015-3033 USA SALES ORDER 16151754/000010	CUSTOMER BILL TO STEEL AND PIPE SUPPLY CO INC MANHATTANKS 66505-1688 USA CUSTOMER MATERIAL N° 000000503003001220	GRADE GGMULTI LENGTH 20'00" SPECIFICATION / DATE OF REVISION ASTM A529-19, A572-21E1 ASTM A6-24A, A36-19, ASME SA36 ASTM A709-21, AASHTO M270-20 CSA G40.20-13 G40.21-13 (R23)
CUSTOMER PURCHASE ORDER NUMBER G450049721		DOCUMENT ID: 0000812207
BILL OF LADING 1333-0000287987		SHAPE / SIZE Angle / 3X3X3/8 WEIGHT 8,640 LB HEAT / BATCH 63263074/02
DATE 08/19/2026		

CHEMICAL COMPOSITION	P (%)	S (%)	Si (%)	Cu (%)	Ni (%)	Cr (%)	Mo (%)	V (%)	Nb (%)	Al (%)	CEqvA529 (%)	CEqvA6 (%)	Sn (%)
C (%)	0.12	0.69	0.013	0.18	0.34	0.09	0.17	0.020	0.004	0.007	0.002	0.34	0.009
Mn (%)	26.00												
Elong. (%)	26.00												

MECHANICAL PROPERTIES	G/L (Inches)	G/L (mm)	UTS (PSI)	UTS (MPa)	YS (PSI)	YS (MPa)
	8.000	200.0	74196	512	54423	375
	8.000	200.0	74297	512	54737	377

COMMENTS / NOTES

This grade meets the requirements for the following grades:
ASTM Grades: A36; A529-50; A572-50; A709-36; A709-50
CSA Grades: 44W; 50W
AASHTO Grades: M270-36; M270-50
ASME Grades: SA36

Gerdaul's steel is 100% recyclable. Support the circular economy through our Metals Recycling Partnership. For details, visit www2.gerdau.com/metals-recycling, or contact metalsrecycling@gerdau.com.

The above figures are certified chemical and physical test records as contained in the permanent records of the company. We certify that these data are correct and in compliance with specified requirements. No weld repair was performed on this material. The material has not been in contact with mercury while in Gerdaul's possession. For all products other than billets or beam blanks, this material was Melted & Poured (via Electric Arc Furnace and Continuous Caster) and produced (Hot Rolled and, if applicable, Cold-Drawn) in the USA. For billets or beam blanks, this material was Melted & Poured (via Electric Arc Furnace and Continuous Caster) in the USA. CMTR complies with EN 10204 3.1.

Ben Lovell
BEN LOVELL
QUALITY DIRECTOR

Phone: (731) 423-5213 Email: benjamin.lovell@gerdau.com

Jorge Huff
JORGE HUFF
QUALITY ASSURANCE MGR.

Phone: (731) 343-8518 Email: jorge.huff@gerdau.com