



US-ML-JACKSON TN
801 GERDAU AMERISTEEL ROAD
JACKSON, TN 38305
USA

CERTIFIED MATERIAL TEST REPORT

CUSTOMER SHIP TO
STEEL AND PIPE SUPPLY CO INC
1003 FORT GIBSON RD
CATOOSA, OK 74015-3033
USA

CUSTOMER BILL TO
STEEL AND PIPE SUPPLY CO INC
MANHATTAN, KS 66505-1688
USA

SALES ORDER
16151754/000010

CUSTOMER MATERIAL N°
000000503003001220

CUSTOMER PURCHASE ORDER NUMBER
G450049721

BILL OF LADING
1333-0000287987

DATE
08/19/2026

GRADE
GGMULTI

LENGTH
20'00"

SHAPE / SIZE
Angle / 3X3X3/8

WEIGHT
8,640 LB

HEAT / BATCH
63263074/02

SPECIFICATION / DATE or REVISION
ASTM A529-19, A572-21E1
ASTM A6-24A, A36-19, ASME SA36
ASTM A709-21, AASHTO M270-20
CSA G40.20-13/G40.21-13 (R23)

CUSTOMER ID:
0000812207

CHEMICAL COMPOSITION		C (%)	Mn (%)	P (%)	S (%)	Si (%)	Cu (%)	Ni (%)	Cr (%)	Mo (%)	V (%)	Nb (%)	Al (%)	CEq _{AS29} (%)	CEq _{AS6} (%)	Sn (%)
0.12	0.69	0.013	0.020	0.18	0.34	0.09	0.17	0.020	0.004	0.002	0.002	0.007	0.002	0.34	0.30	0.009

MECHANICAL PROPERTIES		Elong. (%)	G/L (Inches)	G/L (mm)	UTS (PSI)	UTS (MPa)	YS (PSI)	YS (MPa)
26.00	8.000	200.0	74196	512	54423	375	54737	377
26.00	8.000	200.0	74297	512	54737	375	54737	377

GEOMETRIC CHARACTERISTICS

R/R

14.40

COMMENTS / NOTES

This grade meets the requirements for the following grades:
ASTM Grades: A36, A529-50, A572-50, A709-36, A709-50
CSA Grades: 44W, 50W
AASHTO Grades: M270-36, M270-50
ASME Grades: SA36

GerdaU's steel is 100% recyclable. Support the circular economy through our Metals Recycling Partnership. For details, visit www2.gerdau.com/metals-recycling, or contact metalsrecycling@gerdau.com.

The above figures are certified chemical and physical test records as contained in the permanent records of the company. We certify that these data are correct and in compliance with specified requirements. No weld repair was performed on this material. The material has not been in contact with mercury while in GerdaU's possession. For all products other than billets or beam blanks, this material was Melted & Poured (via Electric Arc Furnace and Continuous Caster) and produced (Hot Rolled and, if applicable, Cold-Drawn) in the USA. For billets or beam blanks, this material was Melted & Poured (via Electric Arc Furnace and Continuous Caster) in the USA. CMTR complies with EN 10204 3.1.

BEN LOVELL
QUALITY DIRECTOR

Phone: (731) 423-5213 Email: benjamin.lovell@gerdau.com

JORGE HUFF
QUALITY ASSURANCE MGR.

Phone: (731) 343-8518 Email: jorge.huff@gerdau.com