

Steel & Pipe Supply Co.
Premier Plant Services
Customer PO: 8643-216092
Heat: 1000237571
Shipment: 0026050051

NUCOR

Mill Certification
07/15/2026

MTR#:2470893-3
Lot #:100023757141
2911 E NUCOR ROAD
PO BOX 309
NORFOLK, NE 68701 US
402 644-0200
Fax: 402 644-0329

Sold To: STEEL & PIPE SUPPLY
555 POYNTZ AVE
PO BOX 1688
MANHATTAN, KS 66502 US

Ship To: TULSA WAREHOUSE
1050 FORT GIBSON RD
CATOOSA, OK 74015 US

Customer PO	4500623812	Sales Order #	10073593 - 1.1
Product Group	Hot Roll - Merchant Bar Quality	Product #	3006306
Grade	Nucor Multigrade	Lot #	100023757141
Size	4" x 4" x 0.25"	Heat #	1000237571
BOL #	BOL-2507337	Load #	2470893
Description	Hot Roll - Merchant Bar Quality Equal Angle 4" x 4" x 1/4" Nucor Multigrade 20' 0" [240"] 2001-6000 lbs	Customer Part #	50400400820
Production Date	06/29/2026	Qty Shipped LBS	33229
Product Country Of Origin	United States	Qty Shipped EA	252
Original Item Description		Original Item Number	

I hereby certify that the material described herein has been manufactured in accordance with the specifications and standards listed above and that it satisfies those requirements.

Melt Country of Origin : United States

Melting Date: 06/25/2026

Roll Country of Origin : United States

Rolling Date: 06/29/2026

C (%)	Mn (%)	P (%)	S (%)	Si (%)	Ni (%)	Cr (%)	Mo (%)	Cu (%)	Ti (%)	V (%)	Nb (%)
0.16	0.65	0.018	0.035	0.20	0.09	0.17	0.03	0.22	0.000	0.016	0.006
Sn (%)	Al (%)										
0.011	0.001										

ASTM A529 S78.2 CE (%) : 0.36

ASTM A992 5.4 CE (%) : 0.33

Reduction Ratio 23.00 : 1

Tensile testing

	Yield (PSI)	Tensile (PSI)	Elongation in 8" (%)
(1)	54900	75400	32.0
(2)	56200	77300	30.0

Comments:

Nucor Multigrade Meets the Requirements of:
ASTM A36/A36M, A529/529M GR50(345), A572/572M GR50(345), A709/709M GR36(250) & GR50(345),
CSA G40.21 GR44W(300W) & GR50W(350W)
AASHTO M270/M270M GR36(270) & GR50(345),
ASME SA36/SA36M
Meets Reporting Requirements of EN10204 SEC 3.1
EN 10204 3.1

Except where noted, all materials melted, cast, and rolled at Nucor Steel Nebraska are produced using an Electric Arc Furnace (EAF) process. Additionally, all manufacturing processes for the steel materials used in this product, including melting, strand casting/pouring, and rolling, have been conducted in the United States.

All products produced are weld free.

Mercury, in any form, has not been used in the production or testing of this material.

Test conform to ASTM A29-23, ASTM E415 and ASTM E1019-resulphurized grades or applicable customer requirements.

Tests included in ISO 17025 scope: Chemistry, Tensile, Brinell Hardness, Rockwell Hardness, Inclusion, and Grain Size.

Exporting Country-USA



NBMG-10 January 1, 2012

Jim Hill, Division Metallurgist

Page 1 of 2