

**Steel & Pipe Supply Co.**  
Premier Plant Services  
Customer PO: 8643-216092  
Heat: 2614433  
Shipment: 0026050051

NUCOR STEEL - BERKELEY  
1455 Regan Avenue  
Foster, SC 29635  
Phone: (843) 335-5000

CERTIFIED MILL TEST REPORT

9/26/26 3:47:34  
100% IAF MELTED AND MANUFACTURED IN THE US  
Structural sections produced by Nucor-Berkeley are cast  
and hot rolled to a fully killed and fine grain practice.  
Mercury not intentionally added at any point during manufacturing.

Sold To: STEEL AND PIPE SUPPLY CO INC  
PO BOX 1688

Ship To: STEEL & PIPE SUPPLY CO., INC.  
1650 FORT GIBSON ROAD

Customer #: 472 - 71  
B.O.L. N... 1932651

MARKING, XS 66585

CATDOGA, CR 74015

MOS: R

SPECIFICATIONS: Tested in accordance with ASTM specification A6/A6M-26 and A370-24a. Tested in accordance with EN10204-2004-3.1.  
Quality Manual Rev A2: (12-13-24).

ASTM: A370-24a

ASTM: A370-24a

CSA: G40.21-05

| Description<br>Part # | Heat<br>Grade(s)<br>Test/Heat | Yield/<br>Tensile<br>Ratio | Yield<br>(PSI)<br>(MPa) | Tensile<br>(PSI)<br>(MPa) | Elong<br>(%) | C<br>Cr | Mn<br>Mn | P<br>P | S<br>S | Si<br>Si | Cu<br>Cu | Ni<br>Ni | CE1<br>CE1 | CE2<br>CE2 |
|-----------------------|-------------------------------|----------------------------|-------------------------|---------------------------|--------------|---------|----------|--------|--------|----------|----------|----------|------------|------------|
| W20X45                | 2514433                       | .77                        | 56300                   | 70400                     | 25.30        | .07     | 1.03     | .012   | .019   | .23      | .13      | .05      | .26        |            |
| 030' 03.00'           | A392-22                       |                            | 374                     | 465                       |              | .05     | .01      | .0056  | .0002  | .002     | .028     |          | .3089      |            |
| W20X45                |                               | .77                        | 55000                   | 71200                     | 26.30        | .07     | 1.03     | .012   | .019   | .23      | .13      | .05      | .26        |            |
| 015.2403m             |                               |                            | 379                     | 491                       |              |         |          | .0011  | .0002  | .0064    |          |          | 3.58       | .1403      |
| 3710390050            |                               |                            |                         |                           |              |         |          |        |        |          |          |          |            |            |
| W20X45                | 1514403                       | .77                        | 52600                   | 69700                     | 24.30        | .07     | 1.06     | .011   | .020   | .27      | .10      | .07      | .26        |            |
| 040' 03.00'           | A392-22                       |                            | 363                     | 474                       |              | .04     | .01      | .0055  | .0004  | .002     | .028     |          | .3146      |            |
| W20X45                |                               | .77                        | 52700                   | 69800                     | 26.30        | .07     | 1.06     | .011   | .020   | .27      | .10      | .07      | .26        |            |
| 012.1923m             |                               |                            | 363                     | 474                       |              |         |          | .0003  | .0004  | .0047    |          |          | 3.02       | .1390      |
| 3710450040            |                               |                            |                         |                           |              |         |          |        |        |          |          |          |            |            |
| W20X45                | 2514433                       | .87                        | 61100                   | 70400                     | 28.30        | .07     | .84      | .008   | .020   | .19      | .17      | .05      | .23        |            |
| 025' 03.00'           | A392-22                       |                            | 421                     | 465                       |              | .05     | .01      | .0063  | .0003  | .002     | .027     |          | .2711      |            |
| W10X21.0              |                               | .87                        | 60000                   | 69900                     | 29.30        | .07     | .84      | .008   | .020   | .19      | .17      | .05      | .23        |            |
| 007.6203m             |                               |                            | 414                     | 475                       |              |         |          | .0007  | .0003  | .0077    |          |          | 4.02       | .1237      |
| 3712140025            |                               |                            |                         |                           |              |         |          |        |        |          |          |          |            |            |

Elongation based on 2' (20.32cm) gauge length. 'No Weld Repair' was performed. All mechanical testing is performed by the Quality Control department. CE1 = C + (Mn/16) + (Cu/20) + (Ni/60) + (Cr/20) + (Mo/15) + (V/10) + Sb. CE2 = C + (Mn/16) + (Cu/20) + (Ni/60) + (Cr/20) + (Mo/15) + (V/10) + Sb.

Nucor certifies that the contents of this report are accurate and correct. All test results and operations performed by the material manufacturer are in compliance with material specifications, and when designated by the purchaser, meet applicable specifications.

Darin M. M...  
Metallography  
Quality Control

*DM*