

CERTIFIED MATERIAL TEST REPORT

 US-ML-MIDLOTHIAN 300 WARD ROAD MIDLOTHIAN, TX 76065 USA		CUSTOMER SHIP TO STEEL AND PIPE SUPPLY CO INC 1003 FORT GIBSON RD CATOOSA, OK 74015-3033 USA		CUSTOMER BILL TO STEEL AND PIPE SUPPLY CO INC MANHATTAN, KS 66505-1688 USA		GRADE A992/A572-50		SHAPE / SIZE Wide Flange Beam / 12 X 40# / 310		DOCUMENT ID: 0001483448	
		SALES ORDER 16300792/000010		CUSTOMER MATERIAL N° 000000003712400060		LENGTH 60'00"		WEIGHT 28,800 LB		HEAT / BATCH 59130865/07	
CUSTOMER PURCHASE ORDER NUMBER G450049969		BILL OF LADING 1327-0000707673		DATE 09/28/2026		SPECIFICATION / DATE or REVISION ASTM A6-24A ASTM A709-21 GR50 ASTM A992-22, A572-21E1 CSA G40.21-13(R23) 345WM, 50W					

CHEMICAL COMPOSITION													
C (%)	Mn (%)	P (%)	S (%)	Si (%)	Cu (%)	Ni (%)	Cr (%)	Mo(%)	Sn (%)	V (%)	Nb (%)	CEqvA6 (%)	
0.08	0.87	0.013	0.022	0.21	0.26	0.11	0.16	0.029	0.009	0.002	0.018	0.29	
MECHANICAL PROPERTIES													
UTS (PSI)		YS (MPa)		UTS (MPa)		Y/T rati (%)		G/L (Inches)		G/L (mm)		Elong. (%)	
YS 0.2% (PSI)		354		464		0.760		8.000		200.0		21.20	
51382		352		456		0.770		8.000		200.0		20.40	
51031													

COMMENTS / NOTES

W 12X40# A992/A572-50 60'00" S
This grade meets the requirements for the following grades:
ASTM Grades: A709-50
CSA Grades: 50W, 50WM, 345WM

Gerdau's steel is 100% recyclable. Support the circular economy through our Metals Recycling Partnership. For details, visit www2.gerdau.com/metals-recycling, or contact metalsrecycling@gerdau.com.

The above figures are certified chemical and physical test records as contained in the permanent records of the company. We certify that these data are correct and in compliance with specified requirements. No weld repair was performed on this material. The material has not been in contact with mercury while in Gerdau's possession. For all products other than billets or beam blanks, this material was Melted & Poured (via Electric Arc Furnace and Continuous Caster) and produced (Hot Rolled and, if applicable, Cold-Drawn) in the USA. For billets or beam blanks, this material was Melted & Poured (via Electric Arc Furnace and Continuous Caster) in the USA. CMTR complies with EN 10204 3.1.

Ben Lovell
BEN LOVELL
QUALITY DIRECTOR
Phone: (731) 423-5213 Email: benjamin.lovell@gerdau.com

Wade Lumpkins
WADE LUMPKINS
QUALITY ASSURANCE MGR.
Phone: 972-799-3118 Email: Wade.Lumpkins@gerdau.com