



CMC STEEL ALABAMA
101 S 50TH STREET
BIRMINGHAM AL 35212-3525

CERTIFIED MILL TEST REPORT
For additional copies call
800-227-6489

We hereby certify that the test results presented here
are accurate and conform to the reported grade specification

Marcus W. McCluney
Marcus W. McCluney - CMC Steel AL
Quality Assurance Manager

1SERIES-BPS®

HEAT NO.:1104933 SECTION: CHANNEL 4"x7.25# 40'0" A36/52950 GRADE: ASTM A36-19/A529-19 Gr50 ROLL DATE: 04/02/2026 MELT DATE: 03/24/2026 Cert. No.: 86933019 / 104933B872		S O L D T O 555 POYNTZ AVE MANHATTAN KS US 66502-6085 7855875182 7855872282		S H I P T O 1003 Fort Gibson Rd Catoosa OK US 74015-0000 9182666325		Steel & Pipe Supply Co Inc Steel & Pipe Supply Co Delivery#: 86933019 BOL#: 77287203 CUST PO#: 4500625583 CUST P/N: 25472540 DLVRY LBS / HEAT: 10440.000 LB DLVRY PCS / HEAT: 36 EA Prod LBS/HEAT: 122090 LB	
Characteristic		Value		Characteristic		Value	
C	0.12%	Elongation Gage Lgth test 1		8IN		The Following is true of the material represented by this MTR: *Material is fully killed and is Hot Rolled Steel *100% melted, rolled, and manufactured in the USA *EN10204:2004 3.1 compliant *Contains no weld repair *Contains no Mercury contamination *Manufactured in accordance with the latest version of the plant quality manual *Meets the "Buy America" requirements of 23 CFR635-410, 49 CFR 66, and the Build America, Buy America Act of 2021 *Warning: This product can expose you to chemicals which are known to the State of California to cause cancer, birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov *THE RECORDING OF FALSE, FICTITIOUS OR FRAUDULENT STATEMENTS OR ENTRIES ON THIS DOCUMENT MAY BE PUNISHABLE AS A FELONY UNDER FEDERAL STATUTE AS A FELONY UNDER FEDERAL STATUTE	
Mn	0.63%	Yield to tensile ratio test1		0.72			
P	0.015%	Yield Strength test 2		51.7ksi			
S	0.026%	Tensile Strength test 2		70.6ksi			
Si	0.16%	Elongation test 2		25.0%			
Cu	0.32%	Elongation Gage Lgth test 2		8IN			
Cr	0.16%	Yield to tensile ratio test2		0.73			
Ni	0.14%						
Mo	0.034%						
V	0.005%						
Cb	0.009%						
Sn	0.011%						
B	0.0001%						
Ti	0.001%						
N	0.0067%						
Carbon Eq A6	0.29%						
Carbon Eq A529	0.32%						
Yield Strength test 1	51.1ksi						
Tensile Strength test 1	70.6ksi						
Elongation test 1	25.8%						
1SERIES ALSO MEETS ASTM GRADE A36-19, A529-19 GR50, A572-25 GR50, A709-24 GR36, A709-24 GR50, A992-22, AASHTO M270-23 GR36, M270-23 GR50, CSA G40.21-04 44W, 50W, ASME SA6							

REMARKS : ALSO MEETS ASTM GRADE A36 REV 08, A572-21 GR 50, A709-36, A709-50, A992, AASHTO GRADE M270-36, M270-50, CSA G40.21-04 GRADE 44W, 50W, ASME SA-36 2008A ADDEND A.