



CMC STEEL TEXAS
1 STEEL MILL DRIVE
SEGUIN TX 78155-7510

CERTIFIED MILL TEST REPORT
For additional copies call
800-227-8489

We hereby certify that the test results presented here
are accurate and conform to the reported grade specification

Drew M Fischer

Drew M Fischer

1SERIES-BPS®

Quality Assurance Manager

HEAT NO.:3134813 SECTION: FLAT 1/4x4 20'0" A36/52950 GRADE: ASTM A36-19/A529-19 GR 50 ROLL DATE: 11/10/2024 MELT DATE: 11/02/2024 Cert. No.: 86157972 / 134813A934		S O L D T O Steel & Pipe Supply Co Inc 555 POYNTZ AVE MANHATTAN KS US 66502-6085 7855875182 7855872282		S H I P T O Steel & Pipe Supply Co 1003 Fort Gibson Rd Catoosa OK US 74015-0000 9182666325		Delivery#: 86157972 BOL#: 76416893 CUST PO#: 4500590521 CUST P/N: 10840020 DLVRY LBS / HEAT: 22440.000 LB DLVRY PCS / HEAT: 330 EA	
Characteristic		Value		Characteristic		Value	
C	0.10%	Tensile Strength test 2		74.4ksi		The Following is true of the material represented by this MTR: *Material is fully killed and is Hot Rolled Steel *100% melted, rolled, and manufactured in the USA *EN10204:2004 3.1 compliant *Contains no weld repair *Contains no Mercury contamination *Manufactured in accordance with the latest version of the plant quality manual *Meets the "Buy America" requirements of 23 CFR635.410, 49 CFR 661 *Warning: This product can expose you to chemicals which are known to the State of California to cause cancer, birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov *THE RECORDING OF FALSE, FICTITIOUS OR FRAUDULENT STATEMENTS OR ENTRIES ON THIS DOCUMENT MAY BE PUNISHABLE AS A FELONY UNDER FEDERAL STATUTE	
Mn	0.78%	Elongation test 2		30%			
P	0.014%	Elongation Gage Lgth test 2		8IN			
S	0.032%						
Si	0.21%						
Cu	0.32%						
Cr	0.17%						
Ni	0.12%						
Mo	0.048%						
V	0.000%						
Cb	0.014%						
Sn	0.010%						
Al	0.001%						
Carbon Eq F1554	0.26%						
Carbon Eq A529	0.34%						
Yield Strength test 1	57.0ksi						
Tensile Strength test 1	73.9ksi						
Elongation test 1	30%						
Elongation Gage Lgth test 1	8IN						
Yield Strength test 2	56.4ksi						

REMARKS : ALSO MEETS ASTM GRADE A36, A529-50, A572-50, A709-36, A709-50, A992, AASHTO M270-36, M270-50, CSA G40.21-04 44W, 50W
ALSO MEETS THE REQUIREMENTS OF ASME SA36