



CMC STEEL TEXAS
1 STEEL MILL DRIVE
SEGUIN TX 78155-7510

CERTIFIED MILL TEST REPORT
For additional copies call
800-227-6489

We hereby certify that the test results presented here
are accurate and conform to the reported grade specification

Thomas Brun

Thomas Brun

Quality Assurance Manager

1SERIES-BPS®

HEAT NO.: 3149194	S	Steel & Pipe Supply Co Inc	S	Steel & Pipe Supply Co	Delivery#: 86972210
SECTION: FLAT 1/4x4 20"0" A36/52950	O		H		BOL#: 77330793
GRADE: ASTM A36-19/A529-19 GR 50	L	555 POYNTZ AVE	I	1003 Fort Gibson Rd	CUST PO#: 4500627325
ROLL DATE: 07/23/2026	D	MANHATTAN KS	P	Catoosa OK	CUST P/N: 10840020
MELT DATE: 07/14/2026	T	US 66502-6085	T	US 74015-0000	DLVRY LBS / HEAT: 4420.000 LB
Cert. No.: 86972210 / 149194A934	O	7855875182	O	9182666325	DLVRY PCS / HEAT: 65 EA
		7855872282			Prod LBS/HEAT: 237932 LB

Characteristic	Value	Characteristic	Value	Characteristic	Value	
C	0.11%	Tensile Strength test 2	77.2ksi	The Following is true of the material represented by this MTR: *Material is fully killed and is Hot Rolled Steel *100% melted, rolled, and manufactured in the USA *EN10204:2004 3.1 compliant *Contains no weld repair *Contains no Mercury contamination *Manufactured in accordance with the latest version of the plant quality manual *Meets the "Buy America" requirements of 23 CFR635.410, 49 CFR 661, and the Build America, Buy America Act of 2021 *Warning: This product can expose you to chemicals which are known to the State of California to cause cancer, birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov *THE RECORDING OF FALSE, FICTITIOUS OR FRAUDULENT STATEMENTS OR ENTRIES ON THIS DOCUMENT MAY BE PUNISHABLE AS A FELONY UNDER FEDERAL STATUTE AS A FELONY UNDER FEDERAL STATUTE		
Mn	0.90%	Elongation test 2	26.4%			
P	0.013%	Elongation Gage Lgth test 2	8IN			
S	0.038%					
Si	0.17%					
Cu	0.38%					
Cr	0.14%					
Ni	0.18%					
Mo	0.064%					
V	0.000%					
Cb	0.015%					
Sn	0.014%					
Al	0.002%					
Carbon Eq F1554	0.29%					
Carbon Eq A529	0.37%					
Yield Strength test 1	55.1ksi					
Tensile Strength test 1	75.7ksi					
Elongation test 1	26.6%					
Elongation Gage Lgth test 1	8IN					
Yield Strength test 2	54.8ksi					
SERIES ALSO MEETS ASTM GRADE A36-19, A529-19 GR50, A572-25 GR50, A709-24 GR50, A709-24 GR36, A709-24 GR50, A992-22, AASHTO M270-23 GR36, M270-23 GR50, CSA G40.21-044W, 50W, ASME SA6						

1SERIES ALSO MEETS ASTM GRADE A36-19, A529-19 GR50, A572-25 GR50, A709-24 GR36, A709-24 GR50, A992-22, AASHTO M270-23 GR36, M270-23 GR50, CSA G40.21-04 44W, 50W, ASME SA6

REMARKS : ALSO MEETS ASTM GRADE A36, A529-50, A572-50, A709-36, A709-50, A992, AASHTO M270-36, M270-50, CSA G40.21-04 44W, 50W
ALSO MEETS THE REQUIREMENTS OF ASME SA36