



CMC STEEL TEXAS
1 STEEL MILL DRIVE
SEGUIN TX 78155-7510

CERTIFIED MILL TEST REPORT
For additional copies call
800-227-6489

We hereby certify that the test results presented here
are accurate and conform to the reported grade specification

Thomas Bruns

Thomas Bruns

Quality Assurance Manager

1SERIES-BPS®

HEAT NO.: 3149265	S	Steel & Pipe Supply Co Inc	S	Steel & Pipe Supply Co	Delivery#: 86972210
SECTION: FLAT 1/4x4 20"0" A36/52950	O	555 POYNTZ AVE	H	I	BOL#: 77330793
GRADE: ASTM A36-19/A529-19 GR 50	L	MANHATTAN KS	P	P	CUST PO#: 4500627325
ROLL DATE: 07/22/2026	D	US 66502-6085	T	O	CUST P/N: 10840020
MELT DATE: 07/17/2026	T	7855875182			DLVRY LBS / HEAT: 40392.000 LB
Cert. No.: 86972210 / 149265A934	O	7855872282			DLVRY PCS / HEAT: 594 EA
					Prod LBS/HEAT: 148104 LB

Characteristic		Value	Characteristic	Value
C	0.10%	Tensile Strength test 2 76.1ksi Elongation test 2 26.3% Elongation Gage Lgth test 2 8IN	The Following is true of the material represented by this MTR: *Material is fully killed and is Hot Rolled Steel *100% melted, rolled, and manufactured in the USA *EN10204:2004 3.1 compliant *Contains no weld repair *Contains no Mercury contamination *Manufactured in accordance with the latest version of the plant quality manual *Meets the "Buy America" requirements of 23 CFR635.410, 49 CFR 661, and the Build America, Buy America Act of 2021 *Warning: This product can expose you to chemicals which are known to the State of California to cause cancer, birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov *THE RECORDING OF FALSE, FICTITIOUS OR FRAUDULENT STATEMENTS OR ENTRIES ON THIS DOCUMENT MAY BE PUNISHABLE AS A FELONY UNDER FEDERAL STATUTE	AS A FELONY UNDER FEDERAL STATUTE AASHTO M270-23 GR36, M270-23 GR50, CSA G40.21-0
Mn	0.79%			
P	0.019%			
S	0.021%			
Si	0.19%			
Cu	0.33%			
Cr	0.13%			
Ni	0.17%			
Mo	0.055%			
V	0.000%			
Cb	0.015%			
Sn	0.011%			
Al	0.002%			
Carbon Eq F1554	0.26%			
Carbon Eq A529	0.34%			
Yield Strength test 1	57.5ksi			
Tensile Strength test 1	75.4ksi			
Elongation test 1	28.6%			
Elongation Gage Lgth test 1	8IN			
Yield Strength test 2	57.3ksi			
SERIES ALSO MEETS ASTM GRADE A36-19, A572-25 GR50, A709-24 GR36, A709-24 GR50, A992-22, AASHTO M270-23 GR36, M270-23 GR50, CSA G40.21-044W, 50W, ASME SA6				

1SERIES ALSO MEETS ASTM GRADE A36-19, A529-19 GR50, A572-25 GR50, A709-24 GR36, A709-24 GR50, A992-22, AASHTO M270-23 GR36, M270-23 GR50, CSA G40.21-04 44W, 50W, 4 44W, 50W, ASME SA6

REMARKS : ALSO MEETS ASTM GRADE A36, A529-50, A572-50, A709-36, A709-50, A992, AASHTO M270-36, M270-50, CSA G40.21-04 44W, 50W
ALSO MEETS THE REQUIREMENTS OF ASME SA36