



US-ML-JACKSON TN
801 GERDAU AMERISTEEL ROAD
JACKSON, TN 38305
USA

CERTIFIED MATERIAL TEST REPORT

 US-ML-JACKSON TN 801 GERDAU AMERISTEEL ROAD JACKSON, TN 38305 USA		CUSTOMER PURCHASE ORDER NUMBER 4500616883		CUSTOMER SHIP TO STEEL AND PIPE SUPPLY CO INC 1003 FORT GIBSON RD CATOOSA, OK 74015-3033 USA		CUSTOMER BILL TO STEEL AND PIPE SUPPLY CO INC MANHATTAN, KS 66505-1688 USA		GRADE GGMULTI SHAPE / SIZE Flat Bar / 3/8 X 3		DOCUMENT ID: 0000781889	
SALES ORDER 15844438/000010				CUSTOMER MATERIAL N° 000000000101230020				LENGTH 20'00" WEIGHT 39.216 LB		HEAT / BATCH 63261189/02	
CUSTOMER PURCHASE ORDER NUMBER 4500616883				BILL OF LADING 1333-0000279669		DATE 04/16/2026		SPECIFICATION / DATE or REVISION ASTM A529-19, A572-21E1 ASTM A6-24A, A36-19, ASME SA36 ASTM A709-21, AASHTO M270-20 CSA G40.20-13/G40.21-13 (R23)			

CHEMICAL COMPOSITION	C (%)	Mn (%)	P (%)	S (%)	Si (%)	Cu (%)	Ni (%)	Cr (%)	Mo (%)	V (%)	Nb (%)	Al (%)	CEq _{AS} (%)	CEq _{A6} (%)	Sn (%)
	0.12	0.63	0.012	0.024	0.17	0.34	0.15	0.19	0.030	0.002	0.007	0.000	0.33	0.30	0.015

MECHANICAL PROPERTIES	G/L (Inches)	G/L (mm)	UTS (PSI)	UTS (MPa)	YS (PSI)	YS (MPa)
Elong. (%)	8.000	200.0	72404	499	53138	366
	27.00	200.0	72288	498	53026	366

GEOMETRIC CHARACTERISTICS	R/R	24.28
---------------------------	-----	-------

COMMENTS / NOTES	
This grade meets the requirements for the following grades: ASTM Grades: A36, A529-50, A572-50, A709-36, A709-50 CSA Grades: 44W, 50W AASHTO Grades: M270-36, M270-50 ASME Grades: SA36	
Gerdaul's steel is 100% recyclable. Support the circular economy through our Metals Recycling Partnership. For details, visit www2.gerdau.com/metals-recycling , or contact metalsrecycling@gerdau.com .	

The above figures are certified chemical and physical test records as contained in the permanent records of the company. We certify that these data are correct and in compliance with specified requirements. No weld repair was performed on this material. The material has not been in contact with mercury while in Gerdaul's possession. For all products other than billets or beam blanks, this material was Melted & Poured (via Electric Arc Furnace and Continuous Caster) and produced (Hot Rolled and, if applicable, Cold-Drawn) in the USA. For billets or beam blanks, this material was Melted & Poured (via Electric Arc Furnace and Continuous Caster) in the USA. CMTR complies with EN 10204 3.1.

Ben Lovell
BEN LOVELL
QUALITY DIRECTOR
Phone: (731) 423-5213 Email: benjamin.lovell@gerdau.com

Jorge Huff
JORGE HUFF
QUALITY ASSURANCE MGR.
Phone: (731) 343-8518 Email: jorge.huff@gerdau.com