



CMC STEEL TEXAS
1 STEEL MILL DRIVE
SEGUIN TX 78155-7510

CERTIFIED MILL TEST REPORT
For additional copies call
800-227-6489

We hereby certify that the test results presented here
are accurate and conform to the reported grade specification

Thomas Brun

Thomas Brun

1SERIES-BPS®

1SERIES-BPS										Quality Assurance Manager					
HEAT NO.:3149265				S		Steel & Pipe Supply Co Inc		S		Steel & Pipe Supply Co		Delivery#: 86972210			
SECTION: FLAT 1/4x4 20"0" A36/52950				O		555 POYNTZ AVE		H		1003 Fort Gibson Rd		BOL#: 77330793			
GRADE: ASTM A36-19/A529-19 GR 50				L		MANHATTAN KS		I		Catoosa OK		CUST PO#: 4500627325			
ROLL DATE: 07/22/2026				D		US 66502-6085		P		US 74015-0000		CUST P/N: 10840020			
MELT DATE: 07/17/2026				T		7855875182		T		9182666325		DLVRY LBS / HEAT: 40392.000 LB			
Cert. No.: 86972210 / 149265A934				O		7855872282		O				DLVRY PCS / HEAT: 594 EA			
												Prod LBS/HEAT: 148104 LB			
Characteristic				Value		Characteristic				Value		Characteristic		Value	
C				0.10%		Tensile Strength test 2				76.1ksi		The Following is true of the material represented by this MTR: *Material is fully killed and is Hot Rolled Steel *100% melted, rolled, and manufactured in the USA *EN10204:2004 3.1 compliant *Contains no weld repair *Contains no Mercury contamination *Manufactured in accordance with the latest version of the plant quality manual *Meets the "Buy America" requirements of 23 CFR 635.410, 49 CFR 661, and the Build America, Buy America Act of 2021 *Warning: This product can expose you to chemicals which are known to the State of California to cause cancer, birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov *THE RECORDING OF FALSE, FICTITIOUS OR FRAUDULENT STATEMENTS OR ENTRIES ON THIS DOCUMENT MAY BE PUNISHABLE AS A FELONY UNDER FEDERAL STATUTE			
Mn				0.79%		Elongation test 2				26.3%					
P				0.019%		Elongation Gage Lgth test 2				8IN					
S				0.021%											
Si				0.19%											
Cu				0.33%											
Cr				0.13%											
Ni				0.17%											
Mo				0.055%											
V				0.000%											
Cb				0.015%											
Sn				0.011%											
Al				0.002%											
Carbon Eq F1554				0.26%											
Carbon Eq A529				0.34%											
Yield Strength test 1				57.5ksi											
Tensile Strength test 1				75.4ksi											
Elongation test 1				28.6%											
Elongation Gage Lgth test 1				8IN											
Yield Strength test 2				57.3ksi											
1SERIES ALSO MEETS ASTM GRADE A36-19, A529-19 GR50, A572-25 GR50, A709-24 GR36, A709-24 GR50, A992-22, AASHTO M270-23 GR36, M270-23 GR50, CSA G40.21-04 44W, 50W, ASME SA6															