



CMC STEEL SOUTH CAROLINA
310 New State Road
Cayce SC 29033-3704

CERTIFIED MILL TEST REPORT
For additional copies call
800-621-0262

We hereby certify that the test results presented here
are accurate and conform to the reported grade specification

Charles T White

Charles T White

Quality Assurance Manager

1SERIES-BPS®

HEAT NO.: 2127007 SECTION: FLAT 1/4x4 20"0" A36/52950 GRADE: ASTM A36-19/A529-19 GR 50 ROLL DATE: 09/09/2026 MELT DATE: 08/31/2026 Cert. No.: 87034823 / 127007D934	S O L D T O	Steel & Pipe Supply Co Inc 555 POYNTZ AVE MANHATTAN KS US 66502-6085 7855875182 7855872282	S H I P T O	Steel & Pipe Supply Co 1003 Fort Gibson Rd Catoosa OK US 74015-0000 9182666325	Delivery#: 87034823 BOL#: 77399993 CUST PO#: 4500631817 CUST P/N: 10840020 DLVRY LBS / HEAT: 39168.000 LB DLVRY PCS / HEAT: 576 EA
Characteristic	Value	Characteristic	Value	Characteristic	Value
C	0.14%	Yield to tensile ratio test1	0.75	The Following is true of the material represented by this MTR: *Material is fully killed and is Hot Rolled Steel *100% melted, rolled, and manufactured in the USA *EN10204 2004 3.1 compliant *Contains no weld repair *Contains no Mercury contamination *Manufactured in accordance with the latest version of the plant quality manual *Meets the "Buy America" requirements of 23 CFR635.410, 49 CFR 661, and the Build America, Buy America Act of 2021 *Warning: This product can expose you to chemicals which are known to the State of California to cause cancer, birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov *THE RECORDING OF FALSE, FICTITIOUS OR FRAUDULENT STATEMENTS OR ENTRIES ON THIS DOCUMENT MAY BE PUNISHABLE AS A FELONY UNDER FEDERAL STATUTE	
Mn	0.65%	Yield Strength test 2	58.0ksi		
P	0.017%	Tensile Strength test 2	77.9ksi		
S	0.028%	Elongation test 2	28.8%		
Si	0.16%	Elongation Gage Lgth test 2	8IN		
Cu	0.36%	Yield to tensile ratio test2	0.74		
Cr	0.19%	C+(Mn/6)	0.25%		
Ni	0.13%				
Mo	0.043%				
V	0.000%				
Cb	0.006%				
Sn	0.012%				
Al	0.001%				
B	0.0003%				
Ti	0.000%				
Carbon Eq A529	0.35%				
Yield Strength test 1	58.0ksi				
Tensile Strength test 1	77.8ksi				
Elongation test 1	30.0%				
Elongation Gage Lgth test 1	8IN				

REMARKS : ALSO MEETS ASTM GRADE A36, A529 GR.50, A572 GR.50, A709 GR.36, A709 GR.50, AASHTO GRADE M270 GR.36, M270 GR.50, CSA G40.21-04 GRADE 44W,50W, ASME SA-36ALSO MEETS F1554 GRADE 36, MIL-S-22698C, REF. QM REV.31, 4/19/24