



CMC STEEL ARIZONA
11444 E. GERMANN RD.
MESA AZ 85212-9700

CERTIFIED MILL TEST REPORT
For additional copies call
800-227-6489

We hereby certify that the test results presented here
are accurate and conform to the reported grade specification

Andrew Huntington
Quality Assurance Manager

1SERIES-BPS®

HEAT NO.: 9013211	S	Steel & Pipe Supply Co Inc	S	Steel & Pipe Supply Co	Delivery#: 87006150
SECTION: CHANNEL 4"x7.25# 40"0"	O		H		BOL#: 77368102
A36/52950	L	555 POYNTZ AVE	I	1003 Fort Gibson Rd	CUST PO#: 4500630282
GRADE: ASTM A36-19/A529-19 Gr50	D	MANHATTAN KS	P	Catoosa OK	CUST P/N: 25472540
ROLL DATE: 05/10/2026	T	US 66502-6085	T	US 74015-0000	DLVRY LBS / HEAT: 17400.000 LB
MELT DATE: 05/10/2026	O	7855875182	O	9182666325	DLVRY PCS / HEAT: 60 EA
Cert. No.: 87006150 / 013211G872		7855872282			Prod LBS/HEAT: 60900 LB

Characteristic		Value	Characteristic		Value	Characteristic	Value
Characteristic	Value	Characteristic	Value				
C	0.12%	Elongation test 2	38.1%	The Following is true of the material represented by this MTR: *Material is fully killed and is Hot Rolled Steel *100% melted, rolled, and manufactured in the USA *EN10204 2004 3.1 compliant *Contains no weld repair *Contains no Mercury contamination *Manufactured in accordance with the latest version of the plant quality manual *Meets the "Buy America" requirements of 23 CFR635.410, 49 CFR 661, and the Build America. Buy America Act of 2021 *Warning: This product can expose you to chemicals which are known to the State of California to cause cancer, birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov *THE RECORDING OF FALSE, FICTITIOUS OR FRAUDULENT STATEMENTS OR ENTRIES ON THIS DOCUMENT MAY BE PUNISHABLE AS A FELONY UNDER FEDERAL STATUTE			
Mn	1.03%	Elongation Gage Lgth test 2	2IN				
P	0.006%						
S	0.018%						
Si	0.25%						
Cu	0.27%						
Cr	0.11%						
Ni	0.09%						
Mo	0.022%						
V	0.049%						
Cb	0.002%						
Sn	0.010%						
Al	0.000%						
Carbon Eq A529	0.39%						
Yield Strength test 1	61.7ksi						
Tensile Strength test 1	78.2ksi						
Elongation test 1	39.3%						
Elongation Gage Lgth test 1	2IN						
Yield Strength test 2	62.2ksi						
Tensile Strength test 2	78.3ksi						

1SERIES ALSO MEETS ASTM GRADE A36-19, A529-19 GR50, A572-25 GR50, A709-24 GR50, A709-24 GR35, A709-24 GR50, A992-22, AASHTO M270-23 GR36, M270-23 GR50, CSA G40.21-04 44W, 50W, ASME SA6

REMARKS :