



CMC STEEL ALABAMA
101 S 50TH STREET
BIRMINGHAM AL 35212-3525

CERTIFIED MILL TEST REPORT
For additional copies call
800-227-6489

We hereby certify that the test results presented here
are accurate and conform to the reported grade specification

M. W. McCluney
Marcus W. McCluney - CMC Steel AL
Quality Assurance Manager

1SERIES-BPS®

HEAT NO.: 1106650	S	Steel & Pipe Supply Co Inc	S	Steel & Pipe Supply	Delivery#: 86958402
SECTION: CHANNEL 6"x10.5# 40'0"	O		H		BOL#: 77314461
A36/572T1	L	555 POYNTZ AVE	I	4750 W Marshall Ave	CUST PO#: 4500627146
GRADE: ASTM A36-19/A572-25e1 Gr50 Tp1	D	MANHATTAN KS	P	Longview TX	CUST P/N: 256105040
ROLL DATE: 06/30/2026	T	US 66502-6085	T	US 75604-4817	DLVRY LBS / HEAT: 20160.000 LB
MELT DATE: 06/28/2026	O	7855875182	O	9037591859	DLVRY PCS / HEAT: 48 EA
Cert. No.: 86958402 / 106650B825		7855872282			

Characteristic		Value	Characteristic		Value
C	0.11%		Yield to tensile ratio test1	0.74	The Following is true of the material represented by this MTR: *Material is fully killed and is Hot Rolled Steel *100% melted, rolled, and manufactured in the USA *EN10204:2004 3.1 compliant *Contains no weld repair *Contains no Mercury contamination *Manufactured in accordance with the latest version of the plant quality manual *Meets the "Buy America" requirements of 23 CFR635.410, 49 CFR 66, and the Build America, Buy America Act of 2021 *Warning: This product can expose you to chemicals which are known to the State of California to cause cancer, birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov *THE RECORDING OF FALSE, FICTITIOUS OR FRAUDULENT STATEMENTS OR ENTRIES ON THIS DOCUMENT MAY BE PUNISHABLE AS A FELONY UNDER FEDERAL STATUTE
Mn	0.86%		Yield Strength test 2	53.5ksi	
P	0.013%		Tensile Strength test 2	72.3ksi	
S	0.022%		Elongation test 2	26.2%	
Si	0.17%		Elongation Gage Lgth test 2	8IN	
Cu	0.30%		Yield to tensile ratio test2	0.74	
Cr	0.20%				
Ni	0.21%				
Mo	0.068%				
V	0.005%				
Cb	0.010%				
Sn	0.010%				
B	0.0002%				
Ti	0.001%				
N	0.0075%				
Carbon Eq A6	0.34%				
Yield Strength test 1	53.4ksi				
Tensile Strength test 1	72.4ksi				
Elongation test 1	25.0%				
Elongation Gage Lgth test 1	8IN				

REMARKS : ALSO MEETS A709 GR. 36, ASME SA36-08 ADDEND A, M270 GR. 36, M270 GR. 50 TYP 1, A709 GR. 50 TYP 1, A529-50, A992, CSA G40.21 GRADE CAN 44W AND CAN 50W