

Steel & Pipe Supply Co.
Premier Plant Services
Customer PO: 9100-216344
Heat: 1000235460
Shipment: 0026051153

NUCOR

Mill Certification

04/29/2026

MTR#:2376846-4
Lot #:100023546043
2911 E NUCOR ROAD
PO BOX 309
NORFOLK, NE 68701 US
402 644-0200
Fax: 402 644-0329

Sold To: STEEL & PIPE SUPPLY
555 POYNTZ AVE
PO BOX 1688
MANHATTAN, KS 66502 US

Ship To: TULSA WAREHOUSE
1050 FORT GIBSON RD
CATOOSA, OK 74015 US

Customer PO	4500620277	Sales Order #	10072272 - 3.1
Product Group	Hot Roll - Merchant Bar Quality	Product #	3006263
Grade	Nucor Multigrade	Lot #	100023546043
Size	3.5" x 3.5" x 0.375"	Heat #	1000235460
BOL #	BOL-2413062	Load #	2376846
Description	Hot Roll - Merchant Bar Quality Equal Angle 3 1/2" x 3 1/2" x 3/8" Nucor Multigrade 20' 0" [240"] 2001-6000 lbs	Customer Part #	503163161220
Production Date	02/17/2026	Qty Shipped LBS	4741
Product Country Of Origin	United States	Qty Shipped EA	28
Original Item Description		Original Item Number	

I hereby certify that the material described herein has been manufactured in accordance with the specifications and standards listed above and that it satisfies those requirements.

Melt Country of Origin : United States

Melting Date: 02/13/2026

Roll Country of Origin : United States

Rolling Date: 02/17/2026

C (%)	Mn (%)	P (%)	S (%)	Si (%)	Ni (%)	Cr (%)	Mo (%)	Cu (%)	Ti (%)	V (%)	Nb (%)
0.16	0.71	0.012	0.022	0.22	0.09	0.17	0.02	0.21	0.000	0.014	0.004
Sn (%)	Al (%)										
0.009	0.002										

ASTM A529 S78.2 CE (%) : 0.38

ASTM A992 5.4 CE (%) : 0.34

Reduction Ratio 18.00 : 1

Tensile testing

	Yield (PSI)	Tensile (PSI)	Elongation in 8" (%)
(1)	53400	74000	29.0
(2)	53300	73800	30.0

Comments:

Nucor Multigrade Meets the Requirements of:

ASTM A36/A36M, A529/529M GR50(345), A572/572M GR50(345), A709/709M GR36(250) & GR50(345),

CSA G40.21 GR44W(300W) & GR50W(350W)

AASHTO M270/M270M GR36(270) & GR50(345),

ASME SA36/SA36M

Meets Reporting Requirements of EN10204 SEC 3.1

EN 10204 3.1

Except where noted, all materials melted, cast, and rolled at Nucor Steel Nebraska are produced using an Electric Arc Furnace (EAF) process.

Additionally, all manufacturing processes for the steel materials used in this product, including melting, strand casting/pouring, and rolling, have been conducted in the United States.

All products produced are weld free.

Mercury, in any form, has not been used in the production or testing of this material.

Test conform to ASTM A29-23, ASTM E415 and ASTM E1019-resulphurized grades or applicable customer requirements.

Tests included in ISO 17025 scope: Chemistry, Tensile, Brinell Hardness, Rockwell Hardness, Inclusion, and Grain Size.

Exporting Country-USA

