

Steel & Pipe Supply Co.
Premier Plant Services
Customer PO: 9100-216344
Heat: 3600059201
Shipment: 0026051153

NUCOR

Mill Certification
09/11/2026

MTR#:2539885-2
Lot #:360005920120
ONE NUCOR WAY
BOURBONNAIS, IL 60914 US
815 937-3131
Fax: 815 939-5599

Sold To: STEEL & PIPE SUPPLY CO INC
PO BOX 1688
MANHATTAN, KS 66502 US

Ship To: STEEL & PIPE SUPPLY CO INC
1050 FORT GIBSON RD
CATOOSA, OK 74015 US

Customer PO	4500629941	Sales Order #	36121206 - 1.1
Product Group	Hot Roll - Merchant Bar Quality	Product #	3005955
Grade	Nucor Multigrade	Lot #	360005920120
Size	3" x 3" x 0.25"	Heat #	3600059201
BOL #	BOL-2580668	Load #	2539885
Description	Hot Roll - Merchant Bar Quality Equal Angle 3" x 3" x 1/4" Nucor Multigrade 20' 0" [240"] 4001-6000 lbs	Customer Part #	50300300820
Production Date	08/03/2026	Qty Shipped LBS	24500
Product Country Of Origin	United States	Qty Shipped EA	250
Original Item Description		Original Item Number	

I hereby certify that the material described herein has been manufactured in accordance with the specifications and standards listed above and that it satisfies those requirements.

Melt Country of Origin : United States

Melting Date: 07/25/2026

Roll Country of Origin : United States

Rolling Date: 08/03/2026

C (%)	Mn (%)	P (%)	S (%)	Si (%)	Ni (%)	Cr (%)	Mo (%)	Cu (%)	Ti (%)	V (%)	Nb (%)
0.11	0.73	0.013	0.030	0.202	0.18	0.16	0.06	0.28	0.000	0.004	0.008

Sn (%)

0.010

ASTM A529 S78.2 CE (%) : 0.34

ASTM A992 5.4 CE (%) : 0.30

Reduction Ratio 20.52 : 1

Tensile testing

	Yield (PSI)	Tensile (PSI)	Elongation in 8" (%)
(1)	56100	75200	29.4
(2)	52900	74500	29.5

Comments:

Nucor Multigrade meets the requirements of: ASTM A36/A36M-19, A529/529M-26 GR50, A572/572M-25 GR50, A709/709M-26 GR36 & GR50 No CVN, CSA G40.21-13 GR44W(300W) & GR50W(350W), AASHTO M270/M270M-23 GR36 & GR50, ASME SA36/SA36M-23.

Meets reporting requirements of EN10204 SEC3.1.

All manufacturing processes of the steel materials in this product, including melting, have occurred within the United States. Products produced are weld free. Mercury, in any form, has not been used in the production or testing of this material. Conforms to the requirements of 23 CFR 635.410 Buy America Requirements.

Zachary Sprintz

Zachary Sprintz, Chief Metallurgist