

Atlas Tube Corp. Kansas City
Burlington St
North Kansas City Missouri USA
64116
Tel:
Fax:



REF B/L: 81326344
Date: 09/26/2025
Customer: 179

Sold To

Steel & Pipe Supply Company
PO Box 1688
MANHATTAN KS 66505
USA

MATERIAL TEST REPORT

Shipped To

Steel & Pipe Supply Company
310 Smith Road
JONESBURG MO 63351
USA

Material: 1.660x140x21"0"(70x1).		Material No: R016601402100-K				Made in: USA											
Sales Order: 2256312		Purchase Order: 4500606026				Melted and Poured in: USA											
Heat No		C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
F03245C25		0.160	0.720	0.006	0.004	0.013	0.041	0.020	0.000	0.000	0.010	0.030	0.000	0.002	0.0001	0.0040	0.0010
Bundle No		PCs	Yield	Tensile	Eln.2in	Method	Recycled_Content	Post_Consumer	Pre_Consumer	ASTM A500-23 GRADE B&C	CE: 0.29						
Z100054244		70	058294 Psi	070295 Psi	29.5 %	BOF	22.90%	9.80 %	13.20%	13.20%	Within Miles of Location						
Heat		MILL	Location	BRADDOCK, PA	88%												
F03245C25		USSTEEL	1000														
Material Note:																	
Sales Or. Note:																	
Material: 1.660x140x21"0"(70x1).		Material No: R016601402100-K				Made in: USA											
Sales Order: 2256312		Purchase Order: 4500606026				Melted and Poured in: USA											
Heat No		C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
F03245C25		0.160	0.720	0.006	0.004	0.013	0.041	0.020	0.000	0.000	0.010	0.030	0.000	0.002	0.0001	0.0040	0.0010
Bundle No		PCs	Yield	Tensile	Eln.2in	Method	Recycled_Content	Post_Consumer	Pre_Consumer	ASTM A500-23 GRADE B&C	CE: 0.29						
Z100054243		70	058294 Psi	070295 Psi	29.5 %	BOF	22.90%	9.80 %	13.20%	13.20%	Within Miles of Location						
Heat		MILL	Location	BRADDOCK, PA	88%												
F03245C25		USSTEEL	1000														
Material Note:																	
Sales Or. Note:																	

Authorized by Quality Assurance: *Jason Richard*
Jason Richard

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type 3.1. Any tubular steel product noted as "Made in USA" and "Melted and Poured in USA" meets the Build America. Buy America Act. Method of manufacture is ERW.

