

**METALLURGICAL
TEST REPORT**

PAGE 1 of 1
DATE 08/26/2026
TIME 06:04:18

S
H
I
P
T
O

13713
Tulsa Warehouse (0020)
1050 Fort Gibson Rd
Catoosa OK 74015-3033

S
O
L
D
T
O

Order	Material No.	Description	Quantity	Weight	Customer Part	Customer PO	Ship Date
40469754-0270	701672144	1/2 72 X 144 A36 STP MIL PLT	4	5,880.960			08/26/2026

Chemical Analysis

Vendor STEEL DYNAMICS COLUMBUS		Mill STEEL DYNAMICS COLUMBUS		Melted and Manufactured in the USA Produced from Coil	
Heat No.	A603812	Carbon	0.0500	Country of Origin: USA	Tin
		Manganese	0.8000	Vanadium	0.0140
		Phosphorus	0.0110	Chromium	0.0010
		Sulphur	0.0020	Aluminum	0.0270
		Silicon	0.0200	Copper	0.1200
		Nickel	0.0400	Boron	0.0001
		Chromium	0.0700	Molybdenum	0.0200
		Molybdenum	0.0200		

Mechanical / Physical Properties

Mill Coil No. 266697626		Yield (PSI)		Tensile (PSI)		Location		Charpy Sz		Temperature	
		69700		69700		35.0		0		NA	
		68700		68700		36.2		0		NA	
		67400		67400		34.9		0		NA	
		69900		69900		34.6		0		NA	

Batch 1002945978 4 EA 5,880.960 LB