

Steel & Pipe Supply Co.
Premier Plant Services
Customer PO: 8643-215406-21
Heat: 7060035
Shipment: 0026038430



CMC STEEL TENNESSEE
1919 Tennessee Avenue
Knoxville TN 37921-2686

CERTIFIED MILL TEST REPORT
For additional copies call
865-867-7366/888-870-0766

We hereby certify that the test results presented here
are accurate and conform to the reported grade specification

Serena Patton

Quality Assurance Manager

HEAT NO.: 7060035 SECTION: REBAR 19MM (#6) 20'0" A615/A706-60 GRADE: ASTM A615&A706-25 GR60 DualGr ROLL DATE: 06/29/2026 MELT DATE: 06/29/2026 Cert. No.: 86898256 / 060035L182		S O L D T O	Adelphia Metals LLC 411 MAIN ST E NEW PRAGUE MN US 56071-2237 9527587500	S H I P T O	CPU Knoxville 2741 MYNDERSE AVE KNOXVILLE TN US 37921-2686 8655460102	Delivery#: 86898256 BOL#: 3468397 CUST PO#: 869702 CUST P/N: DLVRY LBS / HEAT: 17304.000 LB DLVRY PCS / HEAT: 576 EA	
Characteristic		Value	Characteristic		Value	Characteristic	Value
C	0.29%	% Light Test 1 Elongation Gage Lgth 1(metri Bend Test 1 Rebar Deformation Avg. Spaci Rebar Deformation Avg. Heigh Rebar Deformation Max. Gap Uniform Elongation test 1 Deform radius/height ratio 1	5.90%	The Following is true of the material represented by this MTR: *Material is fully killed and is Hot Rolled Steel *100% melted, rolled, and manufactured in the USA *EN10204, 2004 3.1 compliant *Contains no weld repair *Contains no Mercury contamination *Manufactured in accordance with the latest version of the plant quality manual *Meets the "Buy America" requirements of 23 CFR635.410, 49 CFR 66, and the Build America, Buy America Act of 2021 *Warning: This product can expose you to chemicals which are known to the State of California to cause cancer, birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov *THE RECORDING OF FALSE, FICTITIOUS OR FRAUDULENT STATEMENTS OR ENTRIES ON THIS DOCUMENT MAY BE PUNISHABLE AS A FELONY UNDER FEDERAL STATUTE.			
Mn	1.26%		200mm				
P	0.023%		Passed				
S	0.031%		0.436IN				
Si	0.29%		0.056IN				
Cu	0.44%		0.114IN				
Cr	0.24%		11.0%				
Ni	0.09%		1.77				
Mo	0.030%						
V	0.003%						
Sn	0.005%						
Carbon Eq A706	0.54%						
Yield Strength test 1	67.0ksi						
Yield Strength test 1 (metri	462MPa						
Tensile Strength test 1	96.9ksi						
Tensile Strength 1 (metric)	668MPa						
Elongation test 1	16.2%						
Elongation Gage Lgth test 1	8IN						
Tensile to Yield ratio test1	1.45						

REMARKS : MEETS SUPPLEMENTARY REQUIREMENTS OF CURRENT A706 REVISIONS AT THE TIME OF PRODUCTION. MEETS AASHTO M31 TYPE W. 100% MANUFACTURED IN THE USA
PLEASE EMAIL CMC_TN_QUALITY@CMC.COM WITH ANY FEEDBACK, QUESTIONS, OR CONCERNS.