

Steel & Pipe Supply Co.
Premier Plant Services
Customer PO: 8643-215687
Heat: 7060035
Shipment: 0026042160



CMC STEEL TENNESSEE
1919 Tennessee Avenue
Knoxville TN 37921-2686

CERTIFIED MILL TEST REPORT
For additional copies call
865-867-7366/888-870-0766

We hereby certify that the test results presented here
are accurate and conform to the reported grade specification

Serena Patton

Quality Assurance Manager

HEAT NO.:7060035 SECTION: REBAR 19MM (#6) 20'0" A615/A706-60 GRADE: ASTM A615&A706-25 GR60 DualGr ROLL DATE: 06/29/2026 MELT DATE: 06/29/2026 Cert. No.: 86898256 / 060035L182		S Adelphia Metals LLC O L 411 MAIN ST E D NEW PRAGUE MN US 56071-2237 T 9527587500 O		S CPU Knoxville H I 2741 MYNDERSE AVE P KNOXVILLE TN US 37921-2686 T 8655460102 O		Delivery#: 86898256 BOL#: 3468397 CUST POW: 869702 CUST P/N: DLVRY LBS / HEAT: 17304.000 LB DLVRY PCS / HEAT: 576 EA		
Characteristic		Value	Characteristic		Value	Characteristic		Value
C		0.29%	% Light Test 1		5.90%	The Following is true of the material represented by this MTR: *Material is fully killed and is Hot Rolled Steel *100% melted, rolled, and manufactured in the USA *EN10204:2004 3.1 compliant *Contains no weld repair *Contains no Mercury contamination *Manufactured in accordance with the latest version of the plant quality manual *Meets the "Buy America" requirements of 23 CFR635.410, 49 CFR 66, and the Build America, Buy America Act of 2021 *Warning: This product can expose you to chemicals which are known to the State of California to cause cancer, birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov *THE RECORDING OF FALSE, FICTITIOUS OR FRAUDULENT STATEMENTS OR ENTRIES ON THIS DOCUMENT MAY BE PUNISHABLE AS A FELONY UNDER FEDERAL STATUTE.		
Mn		1.26%	Elongation Gage Lgth 1(metri		200mm			
P		0.023%	Bend Test 1		Passed			
S		0.031%	Rebar Deformation Avg. Spaci		0.436IN			
Si		0.29%	Rebar Deformation Avg. Heigh		0.056IN			
Cu		0.44%	Rebar Deformation Max. Gap		0.114IN			
Cr		0.24%	Uniform Elongation test 1		11.0%			
Ni		0.09%	Deform radius/height ratio 1		1.77			
Mo		0.030%						
V		0.003%						
Sn		0.005%						
Carbon Eq A706		0.54%						
Yield Strength test 1		67.0ksi						
Yield Strength test 1 (metri		462MPa						
Tensile Strength test 1		96.9ksi						
Tensile Strength 1 (metric)		668MPa						
Elongation test 1		16.2%						
Elongation Gage Lgth test 1		8IN						
Tensile to Yield ratio test1		1.45						

REMARKS : MEETS SUPPLEMENTARY REQUIREMENTS OF CURRENT A706 REVISIONS AT THE TIME OF PRODUCTION. MEETS AASHTO M31 TYPE W. 100% MANUFACTURED IN THE USA
. PLEASE EMAIL CMC_TN_QUALITY@CMC.COM WITH ANY FEEDBACK, QUESTIONS, OR CONCERNS.