

Steel & Pipe Supply Co.
Premier Plant Services
Customer PO: 8643-216011
Heat: 7059148
Shipment: 0026047713



CMC STEEL TENNESSEE
1919 Tennessee Avenue
Knoxville TN 37921-2686

CERTIFIED MILL TEST REPORT
For additional copies call
865-867-7368/888-870-0766

We hereby certify that the test results presented here
are accurate and conform to the reported grade specification

Serena Patton
Serena Patton
Quality Assurance Manager

HEAT NO.: 7059148 SECTION: REBAR 19MM (#6) 20'0" A615/A706-60 GRADE: ASTM A615/A706-25 GR60 DualGr ROLL DATE: 05/24/2026 MELT DATE: 05/22/2026 Cert. No.: 86830061 / 059148L182		S O L 411 MAIN ST E D NEW PRAGUE MN US 56071-2237 T 9527587500 O		S H I 13535 S Torrence Ave P Chicago IL US 60633-2164 T 7736468363 O		Delivery#: 86830061 BOL#: 3422746 CUST PO#: 867320 CUST P/N: DLVRY LBS / HEAT: 4326.000 LB DLVRY PCS / HEAT: 144 EA
Characteristic	Value	Characteristic	Value	Characteristic	Value	
C	0.27%	% Light Test 1	5.26%	The Following is true of the material represented by this MTR: *Material is fully killed and is Hot Rolled Steel *100% melted, rolled, and manufactured in the USA *EN10204 2004 3.1 compliant *Contains no mold rebar *Contains no Mercury contamination *Manufactured in accordance with the latest version of the plant quality manual *Meets the "Buy America" requirements of 23 CFR 635.416, 49 CFR 66, and the Build America, Buy America Act of 2021 *Warning: This product can expose you to chemicals which are known to the State of California to cause cancer, birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov *THE RECORDING OF FALSE, FICTITIOUS OR FRAUDULENT STATEMENTS OR ENTRIES ON THIS DOCUMENT MAY BE PUNISHABLE AS A FELONY UNDER FEDERAL STATUTE		
Mn	1.28%	Elongation Gage Lgth 1 (metric)	200mm			
P	0.011%	Bend Test 1	Passed			
S	0.026%	Rebar Deformation Avg. Spaci	0.450IN			
Si	0.22%	Rebar Deformation Avg. Height	0.053IN			
Cu	0.27%	Rebar Deformation Max. Gap	0.124IN			
Cr	0.13%	Uniform Elongation test 1	12.2%			
Ni	0.10%	Deform radius/height ratio 1	1.87			
Mo	0.031%					
V	0.003%					
Sn	0.005%					
Carbon Eq A706	0.51%					
Yield Strength test 1	68.2ksi					
Yield Strength test 1 (metric)	470MPa					
Tensile Strength test 1	93.1ksi					
Tensile Strength 1 (metric)	642MPa					
Elongation test 1	14.4%					
Elongation Gage Lgth test 1	8IN					
Tensile to Yield ratio test1	1.37					

REMARKS : MEETS SUPPLEMENTARY REQUIREMENTS OF CURRENT A706 REVISIONS AT THE TIME OF PRODUCTION. MEETS AASHTO M31 TYPE W. 100% MANUFACTURED IN THE USA
PLEASE EMAIL CMC_TN_QUALITY@CMC.COM WITH ANY FEEDBACK, QUESTIONS, OR CONCERNS.