

Atlas Tube Corp. Chicago
1855 East 122nd Street
Chicago Illinois USA
60633
Tel: 773-646-4500
Fax: 773-646-6128



REF B/L: 81405553
Date: 08/25/2026
Customer: 179

Sold To

Steel & Pipe Supply Company
PO Box 1688
MANHATTAN KS 66505
USA

MATERIAL TEST REPORT

Shipped To

Steel & Pipe Supply Company
1020 West Fort Gibson
CATOOSA OK 74015
USA

Material: 3.0x3.0x375x20'0"(6x4).

Sales Order: 2382107

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
Y27028G26	0.180	0.760	0.010	0.007	0.015	0.041	0.040	0.004	0.007	0.010	0.040	0.001	0.001	0.0001	0.0050	0.0000
Bundle No	PCs	Yield	Tensile	Eln.2in												
M801365933	24	075583 Psi	082104 Psi	31 %												
Heat	MILL	MILL Location	Method	Recycled Content	Post_Consumer	Pre_Consumer	CE: 0.32									
Y27028G26	USSTEEL	GARY,IN	BOF	34.20%	19.80%	14.40%	ASTM A500-23 GRADE B&C									
							% Harvested	Within Miles of Location								
							100%	500								
Material Note:																
Sales Or. Note:																

Material: 3.0x3.0x375x20'0"(6x4).

Sales Order: 2382107

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
Y27028G26	0.180	0.760	0.010	0.007	0.015	0.041	0.040	0.004	0.007	0.010	0.040	0.001	0.001	0.0001	0.0050	0.0000
Bundle No	PCs	Yield	Tensile	Eln.2in												
M801365932	24	075583 Psi	082104 Psi	31 %												
Heat	MILL	MILL Location	Method	Recycled_Content	Post_Consumer	Pre_Consumer	(Post Industrial)	% Harvested	Within Miles of Location							
Y27028G26	USSTEEL	GARY,IN	BOF	34.20%	19.80%	14.40%	100%	500								
Material Note:																
Sales Or. Note:																

Authorized by Quality Assurance: *Jason Richard*
Jason Richard

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type 3.1. Any tubular steel product noted as "Made in USA" and "Melted and Poured in USA" meets the Build America. Buy America Act. Method of manufacture is ERW.

