

Testing performed on GraphShield 730

Weathering Resistance QUV-B Resistance – ASTM D-4589 500 hrs

Impact Resistance ASTM D-5420

Solvent Resistance ASTM D-5420 (MEK double rubs)

Appearance PCI Smoothness and PCI Texture; 60° Gloss

Rheology Pill Flow – ASTM D-4242

Thermal Stability Overbake Resistance – ASTM D-2454 (60° gloss, ΔE)

Complete study results are available on request

Corrosion Resistance - Salt Fog (ASTM B117)

- 1,250 hrs. (or until loss of adhesion/pervasive rust)

Testing conducted on:

- Bare cold rolled steel (CRS)
- Fe_3PO_4 treated cold rolled steel

Anticorrosion

Salt fog corrosion results – bare CRS

GraphShield 730 dosage (%)				
0	1	3	5	10
				
Average Creep (mm) on Bare CRS Powder Coated Panels After 250 Hours Exposure to Salt Fog				
2.6	2.0	2.0	1.4	0.4

Corrosion results - Fe₃PO₄ treated CRS

GraphShield 730 dosage (%)				
0	1	3	5	10
				
Average Creep (mm) on Fe ₃ PO ₄ Treated CRS Powder Coated Panels After 1250 Hours Exposure to Salt Fog				
0.8	0.6	0.4	0.6	0.2

GraphShield 730 Anticorrosion results

- **On bare CRS**
 - 1% reduced mm creep by 23%
 - 5% reduced mm creep by 46%
- **On Fe_3PO_4 treated CRS**
 - 1% reduced mm creep by 25%
 - 3% reduced mm creep by 50%