

## MP-28AL Series

Value engineered synthetic wax/aluminum oxide nanocomposites for surface durability and lubricity

### Features and Benefits

- Improves scratch, scuff and mar resistance
- Adds surface slip and lubricity
- Choose XF grade for maximum gloss retention
- Choose G grade for maximum gloss reduction and burnish resistance
- Biodegradable to OECD 302C test standard
- Not a microplastic per ECHA definitions

### Composition

Synthetic wax/aluminum oxide

### Recommended Addition Levels

1.0-3.0% (on total formula weight)

### Systems and Applications

Water based, solvent based and energy curable coatings and inks, Industrial coatings (including plastic, metal and masonry); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; coil coatings.

### Typical Properties\*

|                                   | <u>MP-28AL-XF</u> | <u>MP-28AL</u> | <u>MP-28AL-G</u> |
|-----------------------------------|-------------------|----------------|------------------|
| <b>Mean Particle Size (µm)</b>    | 4.0 - 6.0         | 6.0 - 8.0      | 10.0 - 14.0      |
| <b>Maximum Particle Size (µm)</b> | 15.56             | 22.00          | 44.00            |
| <b>Melting Point °C</b>           | 114 - 118         | 114 - 118      | 114 - 118        |
| <b>Density @ 25 °C (g/cc)</b>     | 0.99              | 0.99           | 0.99             |
| <b>NPIRI Grind</b>                | 1.0 - 2.0         | 1.5 - 3.0      | N/A              |

Mar-26