

SAND FINENESS MODULUS TEST REPORT

Sample Information

Site Name: XYZ	Lot/Truck No: 3327
Supplier: Rudra Mondal	Sample ID: Syllhet
Total Weight: 300 g	Sampling Date: 20 Mar 2025
Testing Date: 21 Sep 2025; 02:08 PM	

Test Results

Fineness Modulus:	2.87
Sand Type:	Medium Sand

Sieve Analysis Data

Sieve Size (mm)	Weight (g)	Cumulative % Retained	% Passing	ASTM Limit
4.75	12	4.04	95.96	95-100%
2.36	14	8.75	91.25	85-100%
1.18	77	34.68	65.32	40-80%
0.60	72	58.92	41.08	20-60%
0.30	72	83.16	16.84	10-40%
0.15	41	96.97	3.03	0-20%
Pan	9	0.00	0.00	0-10%
Total	297.00	286.52		

