Portland Cement CEM I 52.5N

FRT-CEM-I525N · Cement and mortar

Document	Revision	Issue date	Product code
DS-FRT-CEM-I525N	A	2025-06-10	FRT-CEM-I525N

Description

High early strength Portland cement for precast elements, structural concrete and cold-weather work.

Technical properties

Property	Value	Standard
Strength class	52.5 N	EN 197-1
Compressive strength at 2 days	27 MPa	EN 196-1
Compressive strength at 28 days	60 MPa	EN 196-1
Initial setting time	150 min	EN 196-3
Soundness (expansion)	1 mm	EN 196-3

Handling and storage

- Store in a dry place, off the ground. Use within 6 months of the date on the bag.
- Use clean water and mix to a uniform consistency.
- Supplied in 25 kg bags.

Revision history

Revision	Date	Change
A	2025-06-10	First issue.

Values are characteristic or declared values for the product as supplied and do not replace a design check by a qualified engineer. Sample document for demonstration only: the values are illustrative typical figures, not test results.