Masonry Mortar M4 (dry premix)

FRT-CEM-MORM4 · Cement and mortar

Document	Revision	Issue date	Product code
DS-FRT-CEM-MORM4	A	2025-01-03	FRT-CEM-MORM4

Description

General-purpose bricklaying and blocklaying mortar for walls above ground. Add water only.

Technical properties

Property	Value	Standard
Strength class	M4	EN 998-2
Compressive strength at 28 days	4 MPa	EN 1015-11
Setting time (workable life)	120 min	EN 1015-9
Maximum aggregate size	2 mm	EN 1015-1
Dry bulk density	1800 kg/m^3	EN 1015-10

Handling and storage

- Store in a dry place, off the ground. Use within 6 months of the date on the bag.
- Use clean water and mix to a uniform consistency.
- Supplied in 25 kg bags.

Revision history

Revision	Date	Change
A	2025-01-03	First issue.

Values are characteristic or declared values for the product as supplied and do not replace a design check by a qualified engineer. Sample document for demonstration only: the values are illustrative typical figures, not test results.