Ready-Mix Concrete C25/30

FRT-CON-C2530 · Concrete

Document	Revision	Issue date	Product code
DS-FRT-CON-C2530	A	2025-11-17	FRT-CON-C2530

Description

General-purpose ready-mix concrete for foundations, ground-bearing slabs and lightly loaded reinforced elements.

Technical properties

Property	Value	Standard
Characteristic compressive strength, cylinder (28 days)	25 MPa	EN 206
Characteristic compressive strength, cube (28 days)	30 MPa	EN 12390-3
Slump class	S3	EN 12350-2
Maximum aggregate size	20 mm	EN 12620
Density	2350 kg/m^3	EN 12390-7
Exposure class	XC2	EN 206

Handling and storage

- Place within 90 minutes of batching. Do not add water on site.
- Compact fully and cure for at least 7 days; protect from frost until the concrete reaches 5 MPa.
- Delivered by truck mixer in loads of up to 8 m^3.

Revision history

Revision	Date	Change
A	2025-11-17	First issue.

Values are characteristic or declared values for the product as supplied and do not replace a design check by a qualified engineer. Sample document for demonstration only: the values are illustrative typical figures, not test results.