Ready-Mix Concrete C32/40

FRT-CON-C3240 · Concrete

Document	Revision	Issue date	Product code
DS-FRT-CON-C3240	C	2026-01-19	FRT-CON-C3240

Description

Structural ready-mix concrete for reinforced beams, columns and suspended slabs, including external elements exposed to rain.

Technical properties

Property	Value	Standard
Characteristic compressive strength, cylinder (28 days)	32 MPa	EN 206
Characteristic compressive strength, cube (28 days)	40 MPa	EN 12390-3
Slump class	S3	EN 12350-2
Maximum aggregate size	20 mm	EN 12620
Density	2380 kg/m^3	EN 12390-7
Exposure class	XC4, XD1	EN 206

Handling and storage

- Place within 90 minutes of batching. Do not add water on site.
- Compact fully and cure for at least 7 days; protect from frost until the concrete reaches 5 MPa.
- Delivered by truck mixer in loads of up to 8 m^3.

Revision history

Revision	Date	Change
A	2024-03-11	First issue.
B	2025-02-03	Mix redesigned with a lower water/cement ratio. Exposure class extended from XC3, XC4 to XC4, XD1.
C	2026-01-19	Aggregate source changed. Density revised from 2400 to 2380 kg/m^3.

Values are characteristic or declared values for the product as supplied and do not replace a design check by a qualified engineer. Sample document for demonstration only: the values are illustrative typical figures, not test results.