Ready-Mix Concrete C40/50

FRT-CON-C4050 · Concrete

Document	Revision	Issue date	Product code
DS-FRT-CON-C4050	A	2025-09-07	FRT-CON-C4050

Description

High-strength ready-mix concrete for heavily loaded columns, transfer structures and elements exposed to chlorides.

Technical properties

Property	Value	Standard
Characteristic compressive strength, cylinder (28 days)	40 MPa	EN 206
Characteristic compressive strength, cube (28 days)	50 MPa	EN 12390-3
Slump class	S4	EN 12350-2
Maximum aggregate size	16 mm	EN 12620
Density	2400 kg/m^3	EN 12390-7
Exposure class	XD3, XS3	EN 206

Handling and storage

- Place within 90 minutes of batching. Do not add water on site.
- Compact fully and cure for at least 7 days; protect from frost until the concrete reaches 5 MPa.
- Delivered by truck mixer in loads of up to 8 m^3.

Revision history

Revision	Date	Change
A	2025-09-07	First issue.

Values are characteristic or declared values for the product as supplied and do not replace a design check by a qualified engineer. Sample document for demonstration only: the values are illustrative typical figures, not test results.