# PIR Insulation Board 80 mm

FRT-INS-PIR080 · Insulation

| Document | Revision | Issue date | Product code |
|---|---|---|---|
| DS-FRT-INS-PIR080 | A | 2024-06-17 | FRT-INS-PIR080 |

## Description

Foil-faced rigid polyisocyanurate board for pitched roofs, cavity walls and floors where thickness is limited.

## Technical properties

| Property | Value | Standard |
|---|---|---|
| Thermal conductivity | 0.023 W/m·K | EN 12667 |
| Reaction-to-fire class | E | EN 13501-1 |
| Compressive strength at 10 % deformation | 140 kPa | EN 826 |
| Density | 32 kg/m$^3$ | EN 1602 |
| Thickness | 80 mm | EN 823 |

## Handling and storage

- Store flat, dry and out of direct sunlight, in the original packaging.
- Cut with a fine-toothed saw or insulation knife. Butt joints tightly.
- Do not leave boards exposed to weather after installation.

## Revision history

| Revision | Date | Change |
|---|---|---|
| A | 2024-06-17 | First issue. |

Values are characteristic or declared values for the product as supplied and do not replace a design check by a qualified engineer. Sample document for demonstration only: the values are illustrative typical figures, not test results.