PIR Insulation Board 80 mm

FRT-INS-PIR080 · Insulation

Document	Revision	Issue date	Product code
DS-FRT-INS-PIR080	C	2026-03-02	FRT-INS-PIR080

Description

Foil-faced rigid polyisocyanurate board for pitched roofs, cavity walls and floors where thickness is limited.

Technical properties

Property	Value	Standard
Thermal conductivity	0.022 W/m·K	EN 12667
Reaction-to-fire class	E	EN 13501-1
Compressive strength at 10 % deformation	150 kPa	EN 826
Density	32 kg/m^3	EN 1602
Thickness	80 mm	EN 823

Handling and storage

- Store flat, dry and out of direct sunlight, in the original packaging.
- Cut with a fine-toothed saw or insulation knife. Butt joints tightly.
- Do not leave boards exposed to weather after installation.

Revision history

Revision	Date	Change
A	2024-06-17	First issue.
B	2025-05-12	New blowing agent. Thermal conductivity improved from 0.023 to 0.022 W/m·K.
C	2026-03-02	Compressive strength at 10 % deformation raised from 140 to 150 kPa after updated type testing.

Values are characteristic or declared values for the product as supplied and do not replace a design check by a qualified engineer. Sample document for demonstration only: the values are illustrative typical figures, not test results.