XPS Insulation Board 50 mm

FRT-INS-XPS050 · Insulation

Document	Revision	Issue date	Product code
DS-FRT-INS-XPS050	A	2025-12-04	FRT-INS-XPS050

Description

Closed-cell extruded polystyrene board for inverted roofs, basement walls and floors under load.

Technical properties

Property	Value	Standard
Thermal conductivity	0.034 W/m·K	EN 12667
Reaction-to-fire class	E	EN 13501-1
Compressive strength at 10 % deformation	300 kPa	EN 826
Density	33 kg/m^3	EN 1602
Thickness	50 mm	EN 823

Handling and storage

- Store flat, dry and out of direct sunlight, in the original packaging.
- Cut with a fine-toothed saw or insulation knife. Butt joints tightly.
- Do not leave boards exposed to weather after installation.

Revision history

Revision	Date	Change
A	2025-12-04	First issue.

Values are characteristic or declared values for the product as supplied and do not replace a design check by a qualified engineer. Sample document for demonstration only: the values are illustrative typical figures, not test results.