Aerated Concrete (AAC) Block 100 mm

FRT-MAS-AAC100 · Masonry

Document	Revision	Issue date	Product code
DS-FRT-MAS-AAC100	A	2025-05-11	FRT-MAS-AAC100

Description

Lightweight autoclaved aerated concrete block for the inner leaf of cavity walls and internal partitions.

Technical properties

Property	Value	Standard
Mean compressive strength	3.6 MPa	EN 772-1
Water absorption	45 %	EN 772-11
Thermal conductivity	0.15 W/m·K	EN 1745
Dimensions (L x W x H)	440 x 100 x 215 mm	EN 772-16
Gross dry density	600 kg/m^3	EN 772-13

Handling and storage

- Keep packs dry and covered until use. Do not lay in temperatures below 3 °C.
- Mix units from at least three packs to avoid colour banding.
- Supplied shrink-wrapped on pallets.

Revision history

Revision	Date	Change
A	2025-05-11	First issue.

Values are characteristic or declared values for the product as supplied and do not replace a design check by a qualified engineer. Sample document for demonstration only: the values are illustrative typical figures, not test results.