Dense Concrete Block 140 mm 7.3N

FRT-MAS-BLK140D · Masonry

Document	Revision	Issue date	Product code
DS-FRT-MAS-BLK140D	A	2025-03-25	FRT-MAS-BLK140D

Description

Dense aggregate concrete block for load-bearing walls, party walls and work below ground.

Technical properties

Property	Value	Standard
Mean compressive strength	7.3 MPa	EN 772-1
Water absorption	7 %	EN 772-11
Thermal conductivity	1.33 W/m·K	EN 1745
Dimensions (L x W x H)	440 x 140 x 215 mm	EN 772-16
Gross dry density	2000 kg/m^3	EN 772-13

Handling and storage

- Keep packs dry and covered until use. Do not lay in temperatures below 3 °C.
- Mix units from at least three packs to avoid colour banding.
- Supplied shrink-wrapped on pallets.

Revision history

Revision	Date	Change
A	2025-03-25	First issue.

Values are characteristic or declared values for the product as supplied and do not replace a design check by a qualified engineer. Sample document for demonstration only: the values are illustrative typical figures, not test results.