Structural Softwood C24 47 x 195

FRT-TIM-C24 · Timber

Document	Revision	Issue date	Product code
DS-FRT-TIM-C24	A	2025-07-09	FRT-TIM-C24

Description

Kiln-dried, strength-graded softwood for floor joists, rafters and stud walls.

Technical properties

Property	Value	Standard
Characteristic bending strength	24 MPa	EN 338
Mean modulus of elasticity	11000 MPa	EN 338
Characteristic density	350 kg/m^3	EN 338
Moisture content	18 %	EN 14081-1
Service class	1 and 2	EN 1995-1-1

Handling and storage

- Store under cover, clear of the ground and stacked on level bearers.
- Protect from rain during construction; allow wetted elements to dry before closing in.
- Supplied strength graded and marked.

Revision history

Revision	Date	Change
A	2025-07-09	First issue.

Values are characteristic or declared values for the product as supplied and do not replace a design check by a qualified engineer. Sample document for demonstration only: the values are illustrative typical figures, not test results.