CLT Panel 120 mm (3-layer)

FRT-TIM-CLT120 · Timber

Document	Revision	Issue date	Product code
DS-FRT-TIM-CLT120	A	2025-09-19	FRT-TIM-CLT120

Description

Cross-laminated timber panel for load-bearing walls, floors and roofs in mass-timber buildings.

Technical properties

Property	Value	Standard
Characteristic bending strength	24 MPa	EN 16351
Mean modulus of elasticity	11600 MPa	EN 16351
Mean density	470 kg/m^3	EN 16351
Moisture content	12 %	EN 16351
Service class	1 and 2	EN 1995-1-1
Thickness	120 mm	-

Handling and storage

- Store under cover, clear of the ground and stacked on level bearers.
- Protect from rain during construction; allow wetted elements to dry before closing in.
- Supplied strength graded and marked.

Revision history

Revision	Date	Change
A	2025-09-19	First issue.

Values are characteristic or declared values for the product as supplied and do not replace a design check by a qualified engineer. Sample document for demonstration only: the values are illustrative typical figures, not test results.