Glulam Beam GL28h 140 x 405

FRT-TIM-GL28H · Timber

Document	Revision	Issue date	Product code
DS-FRT-TIM-GL28H	A	2025-02-26	FRT-TIM-GL28H

Description

Homogeneous glued laminated timber for long-span roof beams, purlins and exposed frames.

Technical properties

Property	Value	Standard
Characteristic bending strength	28 MPa	EN 14080
Mean modulus of elasticity	12600 MPa	EN 14080
Characteristic density	425 kg/m^3	EN 14080
Moisture content	12 %	EN 14080
Service class	1 and 2	EN 1995-1-1

Handling and storage

- Store under cover, clear of the ground and stacked on level bearers.
- Protect from rain during construction; allow wetted elements to dry before closing in.
- Supplied strength graded and marked.

Revision history

Revision	Date	Change
A	2025-02-26	First issue.

Values are characteristic or declared values for the product as supplied and do not replace a design check by a qualified engineer. Sample document for demonstration only: the values are illustrative typical figures, not test results.