

GOLDEN BASECOAT



PRODUCT DESCRIPTION:

GP-400 is a base coat color mixing system that offers solid color base pigmented, metallic, xirllic and pearl color effect. Golden base coat is used in combination with recommended golden clear coat to give hardness and gloss finish.



Materials for application:

GP-400 Golden Base Coat
GP 901,902,903 golden thinner.
GP-700, GP-701 Clear Coat.
GP-501,502,503, 553 Hardener.



Surface preparation:

Degrease and dry flat with p400 sand paper or wet flat with p1000 sand paper. Apply 2 coats of GP-310.
Sand with p360-p400 for dry flat or p800-p1000 for wet flat.
Apply 2 or 3 single coats of GP-400.



Mixing ratio:

Basecoat: 100
Thinner: 100



Spray viscosity:

15-17 sec / ford cup no.4 @25 c



Spray conditions:

Page 36





Application process:

Apply 2-3 single flowing coats depending on the hiding power of the color.
Allow 5-10 min for flash off time between coats.
Spray the Golden Clear Coat after 20 min of drying the Basecoat.



Drying times:

Drying	25C	60C
Flash off	5-10 min	-
Dust free	5-10 min	-
Dry to handle	-	-
Dry to sand	-	-
Dry to polish	-	-



Cleaning of equipment:

Tools should be cleaned immediately after use with GP-903 thinner.



Physical properties:

Color	As per shade card product
Gloss	Matt
Volume solid Metallic	12 (ASTM D2697)
Coverage	6m ² /l @20 Mm
Sp.gr	-
Flash point	21-25
packaging	1&3.6 liter
Shelf life	24 months