

JAC® SERILUX 72100

Material Data Sheet | White, gloss self-adhesive flexible PVC (approx. RAL 9016) | Manufacturer: Avery Dennison / JAC Graphics

Product Description

JAC® SERILUX is a series of flexible PVC self-adhesive films. JAC SERILUX films display a high degree of tear resistance and tear propagation resistance. They also display relatively good ageing stability, water resistance and light-fastness, depending on the actual applications for which they are used. They are used for the production of high-quality labels for indoor and outdoor application. For optimal UV offset printing results, JAC® SERILUX PLUS is recommended; the same applies for conventional offset.

SERILUX Series — Available Print Carriers (ex stock)

Reference	Colour / Finish	RAL (approx.)
JAC SERILUX 70100	Crystal clear, gloss	—
JAC SERILUX 72100	White, gloss	RAL 9016
JAC SERILUX 72101	White, matt	RAL 9016
JAC SERILUX 71100	Black, matt	RAL 9011
JAC SERILUX 71102	Black, gloss	RAL 9005
JAC SERILUX 74100	Shell yellow, gloss	RAL 1021
JAC SERILUX 75082	Yellow, gloss	—
JAC SERILUX 78100	Red, gloss	RAL 3000
JAC SERILUX 72200	White, gloss (heavier)	RAL 9016

Print Carrier — Average Values

Type No.	70100	72100	72101	Coloured	72200
Weight (g/m ²)	117	95	112	112	230
Thickness (µm)	90	90	80	80	170
Tensile strength – longitudinal (N/mm ²)	35	35	22	22	20
Tensile strength – transverse (N/mm ²)	28	28	—	—	—
Elongation at break – longitudinal (%)	200	200	200	200	—
Elongation at break – transverse (%)	200	200	—	—	—
Transparency (%)	92	—	—	—	—
Opacity (%)	—	91	94	94	—
Shelf life of laminate ¹ (years)	2	2	2	2	2
Max. outdoor durability ² (years)	2	2	2	2	2

¹ Refers to adhesion and printability when stored in original packaging in dark, dry conditions at a temperature of 22 ± 2 °C and a relative humidity of 50 % ± 5 %.

² Under normal climatic conditions as prevailing in Central Europe.

Available Adhesives

All four listed adhesives are dispersion-based acrylic adhesives. **DURO E 110** is the standard permanent adhesive for flexible PVC films, distinguished by high transparency and UV stability. **DURO E 300 SUPER** displays extremely strong adhesion for use on rough and/or apolar surfaces (e.g. plastic containers).

NONPERM A 2 is the standard removable adhesive, highly transparent, removable from most common substrates up to 6 months after application (Central European conditions). **NONPERM A 5** is a long-term removable adhesive with very good guillotining properties, suitable for wet and dry application, removable from most common substrates up to 1 year after application (Central European conditions).

Adhesive – Average values	E 110	E 300 Super	A 5	A 2
Adhesion (N/25 mm) FTM 1, 24 hrs bond on st. steel	13	17	4.5	5
Tack (N/25 mm) FTM 9 on glass	8	11	3	5
Min. application temperature (°C)	+5	+5	+5	+5
Heat resistance — up to 24 hrs (°C)	+80	+90	+120	+80
Heat resistance — up to 1 hr (°C)	+110	+120	+140	+125
Resistance to cold (°C) ³	–40	–40	–40	–40
Ageing stability■	good	good	good	good
Shelf life of laminate (years)■	2	1	2	2

³ Not fully resistant until adhesion reaches full strength after at least 24 hrs.

■ If not exposed to direct sunlight; applied at room temperature.

■ When stored in original packaging at 22 ± 2 °C, 50 ± 5 % RH.

Silicone Paper (Liner) — B145

B145 is a siliconised, special-purpose lightweight board, wood-free, matt on reverse side, moisture-stabilised through specially impregnated fibres and special coating, hence its excellent flatness.

B145 SPLIT is the same liner, but with scored lines running in machine direction spaced 6.25 cm apart, serving as a peel-off aid. B145 SPLIT is supplied as standard with JAC SERILUX 70100, 72100 (adhesive E 110 and A 2) and JAC SERILUX 72101 (adhesive E 110).

Property	B145
Weight (g/m ²)	128
Thickness (µm)	132

Printing Recommendations

Offset printing: with UV-curing inks that are resistant to plasticiser and suitable for films.

Screen printing: with conventional (solvent-based) and UV-curing inks.

Consult your printing-ink supplier about suitable printing inks. All printing inks should be tested for suitability prior to use. For technical guidance, refer to the manufacturer's website — Downloads » Guidelines for use » Offset / Screen printing.

Guarantee and Liability

All Avery Dennison and JAC statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison and JAC products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purposes. All products are sold subject to Avery Dennison's general terms and conditions of sale.

Source: Datasheet JAC® SERILUX (English) — Avery Dennison / JAC Graphics, issue July 2019. Compiled from the publicly available manufacturer's datasheet for reference. Always verify the latest revision with the supplier.