

TEST REPORT

Report No. : PN:TR:1254006185

DATE : 28/04/2021



PROTEQ AUTO CARE

LOWER GROUND, L-102, PRIME MALL, IRLA ROAD, VILE PARLE WEST
MUMBAI-400056

IN

CONTACT PERSON : NEEL WADKE

THE FOLLOWING SAMPLE(S) WAS/WERE SUBMITTED AND IDENTIFIED BY/ON BEHALF OF THE CUSTOMER AS :

SAMPLE DESCRIPTION Glass Ceramic Shield
COLOUR COLOURLESS
PRODUCTION DATE Jan-21
OEM OTHER
COUNTRY OF ORIGIN INDIA
SAMPLE RECD ON 31/03/2021
TEST(S) REQUESTED PENCIL HARDNESS TEST

TESTING PERIOD : 24/04/2021 – 24/04/2021

PENCIL HARDNESS TEST:

ASTM D 3363 : 2011

Test condition : Test conducted at 23±2°C and 50±5% RH.

Pencil type : Mitsubishi UNI pencil.
Pencil holding angle : 45°
Stroke length : 6.5 mm

Grading scale :
6B · 5B · 4B · 3B · 2B · B · HB · F · H · 2H · 3H · 4H · 5H · 6H
Softer ← → Harder

No. of Sample(s) : 01

Observation :

Sample No.	Hardness	Visual observation
1	9H	No coating damage observed upto 9H.

JOE No. : 2154801136

Page -1 of 2


Control No.:1254505046

This document is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms_and_conditions.htm and Terms and Conditions for electronic documents www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only. This document cannot be reproduced except in full, without prior approval of the Company.



• Test photographs :



Note : Test performed as per the conditions given by the client.

***** End of Report*****

Per pro SGS India Private Ltd.

Khanderao ..

Khanderao Chaugule
Sr. Executive

Email your Test Report Related Enquiries at Feedback.trp@sgs.com