



APLICACIÓN Y SUMINISTROS TEXTILES, S.A.

Av. Camí Reial, 13-15  
08184 PALAU-SOLITÀ I PLEGAMANS  
BARCELONA (SPAIN)  
Teléfono: 34 93 864 71 11 – Fax: 34 93 864 51 04  
e-mail: [chemicals@asutex.es](mailto:chemicals@asutex.es)  
Website: [www.asutex.es](http://www.asutex.es)

## TECHNICAL DATA SHEET

Updated: 08/11/13

Page: 1 of 2

## ACTIVANTE PREND CL

For “bleach” effects with sodium hypochlorite on Jeans.

### SCOPE OF APPLICATION

- Activates chlorine bleaching effect.
- Accelerates Indigo degradation.
- Good level of white.
- Better level of white in shorter time.
- Lower strength loose, when compared with usual bleaching methods.
- We do not recommend its application in “low levels of bleach”, because due its high performance, reproduction lot to lot could be eventually poor.

### CHARACTERISTICS

Appearance:	Colourless to lightly yellowish liquid
Ionic character:	Cationic
Stability:	
Hard water:	Good
Acids:	Good
Salts:	Good
Freezing:	Changes in the product due to low temperatures are reversible when recovering room temperature

### APPLICATION

#### *Desizing:*

AMILASE PREND at 60°C.

#### *Stone washing:*

STONE WASH PN 10 POLVO (neutral)  
or STONE WASH GN 72 POLVO (neutral)  
or ASUCEL NE LIQUIDO (neutral)  
Application at 55-60°C

LA INFORMACION CONTENIDA EN ESTA HOJA SE BASA EN EL ESTADO ACTUAL DE NUESTROS CONOCIMIENTOS Y NO IMPLICA RESPONSABILIDAD POR NUESTRA PARTE.

THE INDICATIONS GIVEN HEREIN CORRESPOND TO PRACTICAL EXPERIENCES. OWING TO THE DIFFERENCES IN LOCAL CONDITIONS THEY CANNOT CLAIM TO BE COMPLETE, SO THAT ANY LIABILITIES – ALSO WITH A VIEW TO CLAIMS OF THIRD PARTIES – ARE EXCLUDED.



APLICACIÓN Y SUMINISTROS TEXTILES, S.A.

Av. Camí Reial, 13-15  
08184 PALAU-SOLITÀ I PLEGAMANS  
BARCELONA (SPAIN)  
Teléfono: 34 93 864 71 11 – Fax: 34 93 864 51 04  
e-mail: [chemicals@asutex.es](mailto:chemicals@asutex.es)  
Website: [www.asutex.es](http://www.asutex.es)

## TECHNICAL DATA SHEET

Updated: 08/11/13

Page: 2 of 2

### *Bleach:*

5 cc/L Sodium hypochlorite 15%  
0,5 – 1 cc/L **ACTIVANTE PREND CL**  
15 – 30 minutes at 30 – 40°C  
Rinse  
Anti-chlorine with sodium bisulphite or hydrogen peroxide  
Rinsing and softening:  
ASUMIN C

### APPLICATION OF BLEACH ON GARMENTS CONTAINING LYCRA

It is well known that chlorine damages elastomeric fibres, degrading its elasticity.  
For “bleach” treatments of CO/Lycra, it is recommended CLEARASE